



BUREAU OF ANALYSED SAMPLES LTD

Directors:-
 P.D.RIDSDALE, *BSc, FRSC, CEng, MIM*, (Chairman)
 R.P.MEERES, *BA (Oxon), MRSC* (Managing)
 G.C.FLINTOFT, *ACMA*



Certificate No. GB94/3993

BRITISH CHEMICAL STANDARD CERTIFIED REFERENCE MATERIAL

CERTIFICATE OF ANALYSIS

BCS^{*}/SS[§]-CRM No. 407/2

LOW ALLOY STEEL

Prepared under rigorous laboratory conditions and, AFTER CERTIFICATION ANALYSIS IN GREAT BRITAIN,
 issued by the Bureau of Analysed Samples Ltd.

CO-OPERATING ANALYSTS AND FIRMS

INDEPENDENT ANALYSTS

- 1 HAGGAN, F., *BSc*, AMTAC Laboratories Ltd., Altrincham.
- 2 HEYWOOD, D., *AMet*, Pattinson & Stead, Middlesbrough.
- 3 KENNEDY, J.S., *LRSC*, BCIRA, Birmingham.
- 4 PAGE-GIBSON, J.E., *BSc, CChem, MRSC*, Ridsdale & Co. Ltd., Middlesbrough.

GOVERNMENT DEPARTMENT

- 5 FRYER, R.E.J., *BSc, PhD, CChem, MRSC*, Directorate of Quality Assurance/Technical Support, M.O.D., Woolwich.

ANALYSTS representing MANUFACTURERS and USERS

- 6 AMBROSE, A.D., *BSc*, British Steel Technical, Corby Technical Centre, Corby.
- 7 DAVIES, T.D., GKN Technology Ltd., Wolverhampton.
- 8 DYSON, R., British Steel Technical, Swinden Laboratories, Rotherham.
- 9 GULLAND, W.S., British Steel Technical, Welsh Laboratories, Port Talbot.
- 10 HACON, J., *AMet, CEng, FIM*, Rotherham Engineering Steels, Rotherham.
- 10 HANCOCK, R., *BMet, CEng, MIM*, Stocksbridge Engineering Steels, Sheffield.
- 11 SHAW, D.H., Howmet Alloys International, Exeter.

ANALYSES

Mean of 4 values - mass content in %.

Lab No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	Co	Cu	V
1	3.03	0.83	0.532	0.404	0.19
2	0.483	0.68	0.188	0.038	0.040	0.0066
3	3.03	0.83	0.536	0.410	0.19
4	0.491	0.66	0.206	0.039	0.0098	3.03	0.84	0.537	0.043	0.0076	0.399	0.20
5	0.490	0.64	0.196	...	0.0105	0.039	0.0058
6	0.491	0.66	0.196	0.037	0.0107	...	0.83	...	0.038	0.0068	0.394	...
7	0.494	0.67	0.192	0.038	0.0106	0.0070
8	3.01	0.87	0.537	0.389	0.18
9	0.494	0.0106	3.01	0.82	0.516	0.380	0.17
10	0.492	0.66	0.199	0.037	0.0105
11	0.488	0.65	0.187	0.037	0.0110	3.03	0.82	0.524	0.041	0.0072	0.396	0.18
12	3.05	0.82	0.508	0.402	0.19
M_M	0.490	0.66	0.195	0.038	0.0105	3.03	0.83	0.527	0.040	0.0068	0.397	0.19
<i>s_M</i>	0.004	0.02	0.007	0.001	0.0004	0.02	0.02	0.012	0.002	0.0006	0.010	0.01
<i>s_w</i>	0.003	0.01	0.003	0.002	0.0003	0.02	0.01	0.007	0.002	0.0007	0.006	0.01

The following additional information was supplied:- Analyst No 6: N 0.011%

The above figures are those which each Analyst has decided upon after careful verification

M_M: Mean of the intralaboratory means. *s_M*: standard deviation of the intralaboratory means. *s_w*: intralaboratory standard deviation.
 Values given above in small italic type are for information only.

CERTIFIED VALUES (C_v)

mass content in %

	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	Co	Cu	V
C_v	0.490	0.66	0.195	0.038	0.0105	3.03	0.83	0.527	0.040	0.0068	0.397	0.19
C(95%)	0.003	0.02	0.006	0.001	0.0004	0.02	0.02	0.011	0.003	0.0007	0.008	0.01

The half width confidence interval C(95%) = $\frac{t \times s_M}{\sqrt{n}}$ where "t" is the appropriate Student's t value and "n" is the number of acceptable mean values

For further information regarding the confidence interval for the certified value see ISO Guide 35:1989 section 4.

BCS/SS-CRM No. 407/2 LOW ALLOY STEEL

NOTES ON METHODS USED

CARBON

Analysts Nos. 2 and 4 determined carbon by non-aqueous titration according to the British Standard Carbon Method 4*. Nos. 5, 6, 7, 10 and 11 used high frequency combustion/infrared absorption. No. 9 determined carbon coulometrically (Boniface and Jenkins, Analyst, 1971, 96, 37).

SILICON

Analysts Nos. 2, 4, 6, 7, 10 and 11 determined silicon gravimetrically by double dehydration with perchloric acid, according to the British Standard Silicon Method 1*. No. 5 used a molybdenum blue photometric method.

MANGANESE

Analysts Nos. 2 and 7 determined manganese by Flame Atomic Absorption Spectrometry (FAAS). Nos. 4, 5 and 10 determined manganese photometrically, Nos. 4 and 5 after oxidation with potassium periodate according to the British Standard Manganese Method 2*, No. 10 after oxidation with ammonium persulphate. Nos. 6 and 11 used Inductively Coupled Plasma-Optical Emission Spectrometry (ICP-OES).

PHOSPHORUS

All Analysts, except Nos. 6 and 11, determined phosphorus photometrically as phosphovanadomolybdate according to BS 6200:3.24.1:1985 (British Standard Phosphorus Method 2*). Nos. 6 and 11 used ICP-OES

SULPHUR

Analyst No. 4 determined sulphur gravimetrically according to the British Standard Sulphur Method 1*. Nos. 5, 6, 7, 10 and 11 used high frequency combustion/infrared absorption. No. 9 determined sulphur coulometrically.

CHROMIUM

Analysts Nos. 1, 3, 4, 8, 9 and 12 determined chromium titrimetrically with ammonium ferrous sulphate after oxidation with persulphate/silver nitrate. Nos. 1, 8, 9 and 12 followed the procedure of BS 6200:3.10.1:1985, No. 3 the procedure in BCIRA Method A[‡] and No. 4 that of Analoid Method No. 37. No. 11 determined chromium by FAAS.

Analyst No. 8 determined chromium by FAAS and obtained a mean value of 2.99%

Analyst No. 11 also used ICP-OES and obtained a mean value of 3.05%

MOLYBDENUM

Analysts Nos. 1, 3, 4, 8 and 12 determined molybdenum photometrically as oxythiocyanate, No. 3 according to the BCIRA Method B[‡] and Nos. 4 and 8 according to the British Standard Molybdenum Method 1*. Nos. 6, 9, and 11 used ICP-OES.

Analyst No. 8 also determined molybdenum by FAAS and obtained a mean value of 0.82%

NICKEL

Analysts Nos. 1, 11 and 12 determined nickel by FAAS. Nos. 3, 4 and 8 determined nickel titrimetrically after separation with dimethylglyoxime. Nos. 3 and 8 titrated with EDTA. No. 4 dissolved the precipitate in dilute sulphuric acid, boiled with an excess of ferric sulphate and titrated with potassium dichromate (Analoid Method No. 62). No. 9 used ICP-OES

Analyst No. 8 also used FAAS and obtained a mean value of 0.542%.

Analyst No. 11 also used ICP-OES and obtained a mean value of 0.527%.

ALUMINIUM (Total)

Analysts Nos. 2, 4 and 6 determined aluminium by FAAS, No. 6 used an injection technique. No. 5 determined aluminium photometrically according to the British Standard Aluminium Method No. 3*. No. 11 used ICP-OES.

COBALT

Analysts Nos. 2, 4 and 6 determined cobalt by FAAS. No. 5 determined cobalt photometrically according to the British Standard Cobalt Method 1*. No. 11 used ICP-OES.

COPPER

Analysts Nos. 1, 4, 8 and 12 determined copper by FAAS. No. 3 determined copper photometrically with 2,2'-diquinolyly according to BCIRA Method C[‡]. Nos. 6, 9 and 11 used ICP-OES.

Analyst No. 11 also used FAAS and obtained a mean value of 0.394%.

VANADIUM

Analysts Nos. 1 and 4 determined vanadium titrimetrically according to the British Standard Vanadium method 1*. Nos. 3, 9, 11 and 12 used ICP-OES. No. 8 used FAAS.

*Methods for Sampling and Analysis of Iron, Steel and other Ferrous Metals, B.S. Handbook No. 19, published 1970 by the British Standards Institute, London.

‡Chemical Analysis for Iron Foundries, published 1976 by BCIRA.

DESCRIPTION OF SAMPLE

*British Chemical Standard – bottles of 100g chips graded 1700 – 250µm (10 – 60 mesh) for chemical analysis.

§ Spectroscopic Standard – 38 mm diameter discs for spectroscopic analysis

INTENDED USE & STABILITY

The chip sample, BCS-CRM 407/2, is intended for the verification of analytical methods, such as those used by the participating laboratories, for the calibration of analytical instruments in cases where the calibration with primary substances (pure metals or stoichiometric compounds) is not possible and for establishing values for secondary reference materials.

It will remain stable provided that the bottle remains sealed and is stored in a cool, dry atmosphere. When the bottle has been opened the lid should be secured immediately after use. If the contents should become discoloured (e.g. oxidised) by atmospheric contamination they should be discarded.

The disc sample, SS-CRM 407/2, is intended for establishing and checking the calibration of Optical Emission and X-Ray Spectrometers for the analysis of similar materials. The "as received" working surface of the sample should be finished before use to remove any protective coating. It will remain stable provided that it is not subject to excessive heat (e.g., during preparation of the working surface). An area 6mm in diameter in the centre of the disc should be avoided for optical emission spectrometry

TRACEABILITY

The traceability of this CRM is ensured by the use of either stoichiometric analytical techniques or methods which are calibrated against pure metals or stoichiometric compounds.

This Certified Reference Material has been prepared in accordance with the recommendations specified in ISO Guides 30 to 35, available from the International Standards Organisation in Geneva.

NEWHAM HALL, NEWBY,
MIDDLESBROUGH, ENGLAND, TS8 9EA
Email: enquiries@basrid.co.uk
Website: www.basrid.co.uk

For BUREAU OF ANALYSED SAMPLES LTD

P.D. RIDSDALE,
Chairman

Preliminary Edition July 1990
Main Edition July 1991
Revised with C(95%) and s_w values for each certified element February 2006