

ECISS
EUROPEAN COMMITTEE FOR IRON AND STEEL STANDARDISATION
COMITÉ EUROPÉEN DE NORMALISATION DU FER ET DE L'ACIER
EUROPÄISCHES KOMITEE FÜR EISEN-UND STAHLNORMUNG
EUROPEAN CERTIFIED REFERENCE MATERIAL (EURONORM – CRM)

CERTIFICATE OF CHEMICAL ANALYSIS

EURONORM – CRM No. 087-1 0.15% CARBON STEEL

LABORATORY MEANS (4 Values)
mass content in %

Line No	C	Si	Mn	P	S	Cr	Mo	Ni	As	Co	Cu	Sn	Sb
1	—	0.2558	—	0.0088	0.0426	0.0729	0.0177	—	—	0.0122	—	0.0156	0.0036
2	0.1682	0.2580	0.6590	0.0093	0.0434	0.0738	0.0186	0.1105	—	0.0134	0.1640	0.0158	0.0040
3	0.1690	0.2580	0.6600	0.0093	0.0445	0.0750	0.0188	0.1138	0.0216	0.0135	0.1650	0.0159	0.0041
4	0.1690	0.2585	0.6665	0.0095	0.0448	0.0750	0.0188	0.1147	0.0220	0.0135	0.1665	0.0164	0.0043
5	0.1703	0.2602	0.6668	0.0099	0.0448	0.0758	0.0192	0.1152	0.0221	0.0135	0.1668	0.0164	0.0044
6	0.1706	0.2605	0.6675	0.0100	0.0450	0.0767	0.0194	0.1160	0.0225	0.0136	0.1672	0.0165	0.0044
7	0.1712	0.2610	0.6685	0.0101	0.0450	0.0769	0.0195	0.1170	0.0231	0.0139	0.1675	0.0167	0.0045
8	0.1716	0.2613	0.6688	0.0102	0.0452	0.0778	0.0196	0.1174	0.0232	0.0143	0.1691	0.0167	0.0045
9	0.1718	0.2628	0.6700	0.0102	0.0452	0.0778	0.0198	0.1175	0.0235	0.0144	0.1692	0.0168	0.0046
10	0.1722	0.2632	0.6700	0.0103	0.0454	0.0778	0.0199	0.1175	0.0235	0.0144	0.1695	0.0171	0.0047
11	0.1738	0.2635	0.6704	0.0104	0.0456	0.0789	0.0200	0.1176	0.0238	0.0148	0.1700	0.0172	0.0047
12	0.1740	0.2635	0.6720	0.0104	0.0460	0.0798	0.0204	0.1178	0.0242	0.0149	0.1710	0.0175	0.0048
13	0.1741	0.2648	0.6725	0.0107	0.0462	0.0798	0.0204	0.1180	0.0243	0.0151	0.1715	0.0175	0.0048
14	0.1746	0.2662	0.6728	0.0108	0.0462	0.0808	0.0206	0.1188	0.0248	0.0152	0.1718	0.0175	0.0049
15	0.1758	0.2670	0.6730	0.0109	0.0468	0.0810	0.0215	0.1190	0.0250	0.0155	0.1720	0.0176	0.0049
16	0.1762	0.2672	0.6762	0.0110	0.0472	0.0812	0.0220	0.1195	0.0252	0.0162	0.1728	0.0178	0.0050
17	0.1768	0.2680	0.6770	0.0111	0.0480	0.0823	0.0235	0.1196	0.0254	0.0165	0.1735	0.0180	0.0050
18	0.1772	0.2691	0.6782	0.0118	0.0484	0.0830	0.0235	0.1199	0.0266	0.0166	0.1764	0.0182	0.0052
19	0.1792	0.2700	0.6797	0.0118	0.0484	—	0.0236	0.1227	0.0267	0.0170	0.1802	0.0185	—
20	0.1812	—	0.6815	—	0.0492	—	0.0251	0.1238	0.0270	0.0174	0.1802	0.0192	—
21	0.1842	—	—	—	0.0498	—	—	—	0.0278	—	—	—	—
M_M	0.1740	0.2631	0.6711	0.0103	0.0461	0.0781	0.0206	0.1177	0.0243	0.0148	0.1707	0.0171	0.0046
s_M	0.0043	0.0041	0.0060	0.0008	0.0019	0.0030	0.0020	0.0030	0.0018	0.0014	0.0045	0.0010	0.0004
s_w	0.0017	0.0029	0.0038	0.0004	0.0011	0.0018	0.0006	0.0024	0.0007	0.0004	0.0020	0.0012	0.0003

M_M: Mean of the intralaboratory means, s_M: Standard Deviation of the intralaboratory means.

s_w: Intralaboratory standard deviation, s_b: Interlaboratory standard deviation, $s_b = \sqrt{s_M^2 - (s_w^2 \div 4)}$

The laboratory mean values have been examined statistically to eliminate outlying values. Where a "—" appears in the table it indicates that an outlying value has been eliminated by either the Cochran or Grubbs Test.

CERTIFIED VALUES
Mass content in %

	C	Si	Mn	P	S	Cr	Mo	Ni	As	Co	Cu	Sn	Sb
M_M	0.1740	0.2631	0.6711	0.0103	0.0461	0.0781	0.0206	0.1177	0.0243	0.0148	0.1707	0.0171	0.0046
C(95%)	0.0020	0.0020	0.0029	0.0004	0.0009	0.0015	0.0010	0.0015	0.0009	0.0007	0.0022	0.0005	0.0002

The half-width confidence interval C(95%) = $\frac{t \times s_M}{\sqrt{n}}$ where "t" is the appropriate Student's t value and "n" is the number of acceptable mean values

For further information regarding the confidence interval for the certified value see ISO Guide 35:1989 section 4

This reference material was prepared and issued by:

BUREAU OF ANALYSED SAMPLES LIMITED

Newham Hall, Middlesbrough, England TS8 9EA

On behalf of:- The Iron and Steel Nomenclature Co-ordinating Committee(COCOR) of the ECISS, after approval by all the participating laboratories and all the producing organizations. (France – IRSID/CTIF Germany – Iron and Steel CRM Working Group: VDEh, BAM & MPI für Eisenforschung, Nordic Countries – Nordic CRM Working Group, UK – BAS Ltd.)



Certificate No. Q3993

METHODS USED
EURONORM – CRM No. 087-1

Element	Line Number	Methods
C	2-4-5-16	Combustion, non-aqueous titration
	3	Combustion, low pressure
	6-9-11-13-14-17-19-20-21	Combustion, infrared absorption
	7-12	Combustion, conductimetric
	8-15-18	Combustion, coulometric
	10	Combustion, thermal conductivity
Si	1-3-4-6-8-10-14-16	Photometric, as molybdenum blue
	2-11-15-17-19	Flame atomic absorption spectrometry
	5-7-9-12-13-18	Gravimetric, dehydration with perchloric acid
Mn	2-6-8-9-10-11-13-14-15-16-17-19-20	Photometric, oxidation with periodate
	3-4-5-7-12-18	Flame Atomic Absorption Spectrometry
P	1-2-4-8-9-16-17-18-19	Photometric, as molybdenum blue
	3-6-7-11-13-14-15	Photometric, as phosphovanadomolybdate with extraction
	5	Photometric, as molybdenum blue with extraction
	10-12	Titrimetric as phosphomolybdate
S	1-7	Combustion, acidimetric titration
	2-4-5-6-9-10-11-12-16-18-19-20-21	Combustion, infrared absorption
	3-17	Combustion, conductimetric
	8-14	Combustion, coulometric
	13	Combustion, oxidation/reduction titration
	15	Gravimetric, as barium sulphate
Cr	1-5-6-9-10-11-12-14-16-17-18	Flame Atomic Absorption Spectrometry
	2-3-8-13-15	Photometric, with diphenylcarbazide
	4	Titrimetric with Fe (II), persulphate/silver nitrate oxidation
	7	Photometric, as chromate
Mo	1-2-4-5-9-11-12-14-15-17-19-20	Flame Atomic Absorption Spectrometry
	3-7-8-10-13-16	Photometric, as thiocyanate, with extraction
	6-18	Photometric, as thiocyanate, without extraction
Ni	2-7-10-11-12-16-20	Photometric, with dimethylglyoxime
	3-4-5-6-8-9-13-14-15-17-18-19	Flame Atomic Absorption Spectrometry
As	3-11-15-19-20	Flame Atomic Absorption Spectrometry
	4-5-9-14	Photometric, as silver diethyldithiocarbamate
	6	Hypophosphite reduction, titration with iodine
	7-8-10-12-13-16-18-21	Photometric as molybdenum blue, with extraction
	17	Distillation, titration with bromate
Co	1-2-5-8-10-12-13-14-15-16-17-18-19-20	Flame Atomic Absorption Spectrometry
	3-9	Photometric, with nitroso-R salt after separation with 1-nitroso-2-naphthol
	4-6-7	Photometric, with nitroso-R salt
	11	Photometric, with isonitrosomalonylguanidine
Cu	2-4-5-6-7-10-11-12-14-16-17-18-19	Flame Atomic Absorption Spectrometry
	3	Photometric, with bis-cyclohexanone oxalyldihydrazone
	8	Photometric, with diethyldithiocarbamate
	9	Photometric, with oxalyl dihydrazide
	13-15	Photometric, with 2,2' diquinolyl
	20	Photometric, as cupramine
Sn	1-2-4-7-9-10-11-13-14-15-18	Flame Atomic Absorption Spectrometry
	3-12-19	Iodate titration, reduction with aluminium
	5-6-8-17-20	Photometric, with phenylfluorone
	16	Photometric with dithiol after distillation
Sb	1-2-3-5-7-10-11-12-13-16-17	Flame Atomic Absorption Spectrometry
	4	Photometric, with rhodamine B after distillation
	6-15	Photometric, with brilliant green
	8-9	Photometric, with rhodamine B with extraction
	14-18	Photometric, as iodide

PARTICIPATING LABORATORIES

Arbed, Division d'Esch Belval, Esch-sur-Alzette, Luxembourg
Breda Siderugica, Milan, Italy
British Steel Corporation, Corby Works, UK
British Steel Corporation, River Don Works, Rotherham, UK
British Steel Corporation, Rotherham Works, UK
Bundesanstalt für Materialprüfung (BAM), Berlin, Germany
Centro Sperimentale Metallurgico (CSM), Rome, Italy
Cockerill, Seraing, Belgium
Fried, Krupp Hüttenwerke AG, Werk Rheinhausen, Germany
Hoesch Hüttenwerke AG, Dortmund, Germany
Hoogovens-ESTEL, IJmuiden, Holland
Institute for Industrial Research and Standards (IIRS), Dublin, Eire
Institut de Recherches de la Sidérurgie Française (IRSID),
St. Germaine-en-Laye, France
Laboratoires Boudet et Dussaix, Croissy sur Seine, France
Ridsdale and Co. Ltd., Middlesbrough, UK
Round Oak Steelworks, Brierley Hill, UK
Sacilor, Amneville, France
SNCF, Levallois Perret, France
Société Metallurgique Hainaut Sambre, Couillet, Belgium
Staatliches Materialprüfungsamt NW, Dortmund, Germany
Usinor, Dunkerque, France

INTENDED USE & STABILITY

This sample is intended for the verification of analytical methods, such as those used by the participating laboratories, for the calibration of analytical instruments in cases where the calibration with primary substances (pure metals or stoichiometric compounds) is not possible and for establishing values for secondary reference materials.

It will remain stable provided that the bottle remains sealed and is stored in a cool, dry atmosphere. When the bottle has been opened the lid should be secured immediately after use. If the contents should become discoloured (e.g. oxidised) by atmospheric contamination they should be discarded.

TRACEABILITY

The traceability of this ECRM is ensured by the use of either stoichiometric analytical techniques or methods which are calibrated against pure metals or stoichiometric compounds.

FURTHER INFORMATION

For information regarding the preparation, certification and supply of these European Certified Reference Materials (EURONORM-CRMS) and the use of the statistical information given on this certificate, please refer to CEN Report CR 10317 and ECISS Information Circular No. 5, both of which are available from the national standards body in your country or from CEN in Brussels. (In the UK this is the BSI, 389 Chiswick High Road, London W4 4AL).

Des informations complémentaires sur la fabrication, la certification et la distribution des Matériaux de Référence Certifiés Européens (EURONORM-MRC) ainsi que sur l'utilisation des informations statistiques données sur le certificat se trouvent dans le Rapport CEN CR 10317 et dans la circulaire d'information No. 5 (ECISS). On peut se procurer ces deux documents auprès des organismes nationaux de normalisation ou auprès du CEN, Bruxelles. (Pour la France: AFNOR, 11 Avenue Francis de Pressensé, 93571 – St Denis la Plaine Cedex).

Angaben über Herstellung, Zertifizierung und Bezugsmöglichkeiten dieser Europäischen Zertifizierten Referenzmaterialien (EURONORM-ZRM) sowie über die Anwendungen der in diesem Zertifikat enthaltenen statistischen Daten finden sich im CEN-Report CR 10317 und in der Mitteilung Nr. 5 (ECISS), beide zu beziehen durch die nationalen Normenorganisationen oder direkt von CEN, Brüssel. (In Deutschland bei der Vertriebsstelle des DIN: Beuth-Verlag GmbH, Burggrafenstrasse 4-10, 10787 Berlin).

För information angående tillverkning, certifiering och distribuering av dessa europeiska certifierade referensmaterial (EURONORM CRM) och för användning av statistisk information, som angivits i detta certifikat, refereras till CEN rapport CR 10317 och till informationscirkulär Nr. 5 (ECISS) från den nationella standardiseringsorganisationen eller från CEN, Bruxelles. (I Sverige är det SIS, S:t Paulsgatan 6, SE-118 80 Stockholm, i Finland är det SFS, PL. 116, FIN-002 41, Helsinki, i Danmark är det DS, Kollegievej 6, DK-Charlottenlund 2920, i Norge är det NSF, Drammensveien, 145 A, Postboks 353 Skøyen, NO-0213 Oslo, på Island är det STRI, Holtagardar, IS-104 Reykjavik).

REVISION HISTORY

First Issued February 1980

Reprinted March 1984

Revised with C(95%) and s_w values for each certified element and improved accuracy for all elements except Sb February 2005

NEWHAM HALL, NEWBY,
MIDDLESBROUGH, ENGLAND, TS8 9EA
Email: enquiries@basrid.co.uk
Website: www.basrid.co.uk

For BUREAU OF ANALYSED SAMPLES LTD.

P.D. RIDSDALE,
Chairman