

BUREAU OF ANALYSED SAMPLES LTD

Certified Reference Materials



Catalogue No. 782a

JUNE 2010



4004

Certificate GB94/3993

CONTENTS

	Page		Page
INTRODUCTION	2	SPECTROSCOPIC STANDARD CERTIFIED	
GENERAL INFORMATION	2	REFERENCE MATERIALS	
CO-OPERATING ANALYSTS AND LABORATORIES	3	Plain Carbon Steels	17
		Carbon Steel Residual Series	17
		High Purity Iron	18
		Low Alloy Steels	18
		Low Alloy Cast Steels	18
		Highly Alloyed Steels	19
		Austenitic Stainless Steels	19
		Plain Carbon Cast Steels	19
		Ferritic Stainless Steels	20
		High Speed Tool Steels	20
		High Manganese Cast Steels	20
		Cast Irons	21
		Nickel Base Alloys	21
		SPECTROSCOPIC REFERENCE MATERIALS	
BRITISH CHEMICAL STANDARD AND EURONORM		Low Alloy Cast Irons	22
CERTIFIED REFERENCE MATERIALS		High Chromium Irons	22
High Purity Irons	7	Nickel Chromium Irons	22
Unalloyed Steels	7	Austenitic (Ni-Resist) Irons	22
High Speed Tool Steels	8	Silicon Molybdenum Cast Irons	22
Alloy Steels	9	Phosphorus Deoxidised Coppers	23
Highly Alloyed Steels	10	Main Elements in Brasses	23
Special Alloys	11	Admiralty & Naval Brasses	23
Cast Irons	11	Aluminium Brasses	23
Ferro-Alloys	11	Cartridge Brasses	23
Aluminium Base Alloys	12	Leaded Bronzes	23
Magnesium Base Alloys	12	Aluminium Bronzes	23
Copper Base Alloys	12	Phosphor Bronzes	23
Lead and Tin Base Alloys	13	Cupro Nickel	23
Nickel Base Alloys	13	Leaded Gunmetals	23
Titanium Base Alloys	13	SPECTROSCOPIC SETTING-UP SAMPLES	
Chromium Metal	13	Carbon and Low Alloy Steels	24
Cements	13	Highly Alloyed & Stainless Steels	24
Ores, Fluxes, Dust	14	Cast Irons	24
Slags	14	NUMERICAL INDEX (INCLUDING CERTIFICATION DATES)	25
Tungsten Carbides	14	PURCHASE PROCEDURE	29
Silicon Carbide Refractories	14		
Ceramic Materials	15		
Minerals	15		
Glass Sand	15		
BRITISH CHEMICAL STANDARD REFERENCE MATERIALS			
High Purity Metals	16		
Ceramic Materials	16		
Benzoic Acid	16		

BUREAU OF ANALYSED SAMPLES LTD., NEWHAM HALL, NEWBY, MIDDLESBROUGH, ENGLAND, TS8 9EA.

Telephone: National: Middlesbrough (01642) 300500
International: +44 1642 300500
Website: www.basrid.co.uk

Fax: National: Middlesbrough (01642) 315209
International: +44 1642 315209
Email: enquiries@basrid.co.uk

INTRODUCTION

The Certified Reference Materials have been prepared under rigorous laboratory conditions and are issued by Bureau of Analysed Samples Ltd. under the auspices of an Honorary Advisory Committee and a body of approximately 150 co-operating analysts representing Independent Laboratories and Manufacturers and Users of the materials concerned.

(a) **CERTIFIED REFERENCE MATERIALS (CRMs)**

British Chemical Standard Certified Reference Materials (BCS-CRMs) are normally analysed by at least five analysts, and a certificate showing the individual mean values obtained by each analyst and a summary of the methods used is supplied with each sample. Certificates issued since 1984 also give the standard deviation of the intralaboratory means, and those issued since 1994 express the level of confidence of the certified value as the 95% half width confidence interval.

EURONORM Certified Reference Materials (ECRMs) are prepared under the auspices of the European Committee for Iron and Steel Standardization (ECISS) and are issued with a certificate giving the names of the participating laboratories, the mean values obtained by each laboratory for each element and a statistical evaluation of the laboratory means. The certificate also includes a summary of the methods of analysis used. Before publication each certificate is approved by the four Producing Organisations, namely Bureau of Analysed Samples Ltd. (BAS) in the UK, Institut de Recherches de la Siderurgie Française (IRSID)/Centre de Développement des Industries de Mise en Forme des Matériaux (CTIF) in France, Stahlinstitut VDEh (VDEh), BAM Bundesanstalt für Materialforschung und prüfung and Max-Planck-Institut für Eisenforschung (MPI) in Germany and the Nordic CRM Working Group (NCRMWG) in the Nordic countries.

Pending their eventual replacement by ECRMs, some existing BCS-CRMs have been accepted as interim ECRMs after examination by laboratories in the EU. These are indicated with an ECRM number alongside the existing BCS-CRM number.

Bureau of Analysed Samples Ltd. act as UK distributors for ECRMs prepared by IRSID/CTIF in France, BAM in Germany and Jernkontoret in Sweden, and details of these samples, most of which are held in UK stock, are given in a separate BAS 'Outside Source' Reference Materials Catalogue, copies of which will be supplied on request. Further information regarding the preparation, certification and supply of ECRMs, and the use of the statistical information given on their certificates is given in Technical Reports **CEN/TR 10317:2009** (formerly **ECISS Information Circular No. 1**) and **CEN/TR 10350:2009** (formerly **ECISS Information Circular No. 5**) which are available in the UK from the BSI, 389 Chiswick High Road, London W4 4AL.

All BCS-CRM and ECRM samples are supplied in the finely divided form and many of them are also available in disc form for optical emission and X-ray fluorescence spectrometry.

Spectroscopic Standard Certified Reference Materials (SS-CRMs) have been specially prepared to provide samples of uniform composition in a form suitable for use with optical emission and X-ray fluorescence spectrometers. Each sample has been analysed by at least five laboratories, and a certificate showing the individual mean values obtained by each laboratory and a summary of the methods used is supplied with each sample or set of samples.

Steel samples are usually in the form of discs cut from round bar. Cast iron samples, which are prepared in conjunction with Castings Technology International (formerly BCIRA), are in the form of chill cast rectangular blocks.

(b) **REFERENCE MATERIALS (RMs)**

British Chemical Standard Reference Materials (BCS-RMs) and Spectroscopic Reference Materials, e.g. high purity metals and ceramic materials (p.16), low alloy cast irons, high chromium irons, nickel chromium irons and austenitic (Ni-resist) irons (p. 22) and copper base alloys (p. 23) are normally analysed by only two laboratories and are not given certified status. When the British Non Ferrous Metals Technology Centre (BNF) closed down in 1992, BAS purchased their entire stock of copper, nickel and lead base spectroscopic RMs (see the separate BAS 'Outside Source' Reference Materials Catalogue). When supplies of these have become exhausted BAS have prepared replacements using the same casting techniques as BNF (see p. 23).

(c) **SPECTROSCOPIC SETTING-UP SAMPLES (SUS)**

These Setting-up Samples (SUS) have been specially prepared to meet the day to day setting-up requirements of laboratories using direct reading spectrometers for production control analysis. Their use will conserve supplies of Spectroscopic Standard CRMs for calibration purposes only and will relieve spectrographers of the problem of finding suitable samples within their works for their daily setting-up requirements.

The steel samples are in the form of round bar. The cast iron samples, prepared in conjunction with Castings Technology International (formerly BCIRA), are in the form of chill cast rectangular blocks.

GENERAL INFORMATION

Every endeavour is made to maintain a continuous supply of all samples in this catalogue by completing the preparation of an appropriate replacement by the time each sample becomes exhausted. When orders are received for obsolete samples the relevant replacements will normally be supplied. If for any reason such a sample is not acceptable, full credit will be allowed if it is returned carriage paid provided that the seal on the carton containing finely divided samples is unbroken.

Information regarding new samples in course of preparation will be supplied on request. When these are available for distribution a notice to this effect will be made on our website.

QUALITY ASSURANCE

Bureau of Analysed Samples Ltd. are very pleased to advise that in November 1994 their Quality System was formally approved and recognised by the award of a Certificate of Registration to the Quality Standard BS EN ISO 9002:1994 for the production and supply of CRMs, RMs and SUS. This certificate has now been revalidated to the new Standard BS EN ISO 9001: 2008. Furthermore, they were accredited, in June 2006, to the International Guide, ISO Guide 34:2000.

BUREAU OF ANALYSED SAMPLES LTD.

REG. No. 307549 (ENGLAND)

DIRECTORS

R.P. MEERES, BA (Oxon), MRSC., (Managing Director)

G.C. FLINTOFT, ACMA (Company Secretary)

Mrs J.C. MEERES

M.S. TAYLOR, PhD, CChem, MRSC

HONORARY ADVISORY COMMITTEE

M. ALLEN, Corus Strip Products, Port Talbot

M. BLACKWELL/M. WEBSTER, ATI Allvac Ltd., Sheffield

J.D. HOBSON, BSc, PhD, AMet, CChem, FRSC, Independent Consultant

S. N. JAMIESON, MSc, CChem, MRSC, Pilkington European Technical Centre, Latham

K.M. JOHNSON, BSc, MSc, PhD, Ceram Research Ltd., Stoke-on-Trent

R. JOWITT, ex Corus, Teesside Laboratories, Middlesbrough

G.J. OLIVER, BSc, PhD, CChem., MRSC, Ceram Research Ltd., Stoke-on-Trent

P. RUGG, Corus Engineering Steels, Rotherham

P. SCRIMSHIRE, BSc, IncoTest, Hereford

I. WOODHEAD, Corus Testing Solutions, Scunthorpe

CO-OPERATING ANALYSTS AND LABORATORIES

Analysts and Laboratories Participating in the Analysis of British Chemical Standard and Spectroscopic Standard Certified Reference Materials and EURONORM-CRMs prepared by Bureau of Analysed Samples Ltd.

UK INDEPENDENT ANALYSTS

ALCONTROL LABORATORIES (per **Prof. K.C. Thompson**, BSc, PhD, CChem, FRSC) Rotherham

BRITISH GEOLOGICAL SURVEY (per **Ms. J.M. Cook**, CChem, MRSC) Nottingham

BUTTERWORTH LABORATORIES (per **A. Gilbert & D. Riches**) Teddington

CERAM RESEARCH LTD.

(Per **G.J. Oliver**, BSc, PhD, CChem, MRSC, & **K.M. Johnson**, BSc, MSc, PhD) Stoke-on-Trent

EXOVA TEESSIDE (per **I. Boustead**, BSc & **Miss J. Day**) Middlesbrough

GLASS TECHNOLOGY SERVICES LTD. (per **Mrs. M. Flower**) Sheffield

HARWELL SCIENTIFICS LTD. (per **Ms. J. Haines**) Didcot

INSPECTORATE INTERNATIONAL LTD. (per **K. Blaxall**) Witham

KEIGHLEY LABORATORIES LTD. (per **A. Wade & J.S. Whitaker**) Keighley

KNIGHT INTERNATIONAL LTD., ALFRED H. (per **A.M. Katz & T.A. Sutcliffe**) St. Helens

LGC LTD. (per **S. Wood**, BSc, PhD) Teddington

OPEN UNIVERSITY (per **P.J. Potts**, BSc, PhD, DSc, CChem, FRSC & **P.C. Webb**) Milton Keynes

PATTINSON & STEAD (2005) Ltd. (per **F.H. Crocker**) Middlesbrough

RIDSDALE & CO. LTD. (per **S.J. Jones**, BSc, CChem, MRSC) Middlesbrough

SANDBERG CONSULTING London

SHEFFIELD HALLAM UNIVERSITY (per **R. Burton**) Sheffield

SHEFFIELD TESTING LABORATORIES LTD. (per **J. Hastings**) Sheffield

STEWART, ALEX (ASSAYERS) LTD. (per **K.A. Stewart**, CChem, FRSC, MIMM & **P. Blundell**) . Knowsley

UK ANALYTICAL (per **Ms. S. Atherton**) Leeds

UNIVERSITY OF EXETER (per **Ms. F. Thomas**) Penryn

UNIVERSITY OF LEEDS (per **Ms. L. Neve**, MSc, MRSC) Leeds

UNIVERSITY OF LEICESTER (per **N.G. Marsh**) Leicester

UNIVERSITY OF SHEFFIELD (per **Prof. C.W. Mcleod**) Sheffield

UNIVERSITY OF SOUTHAMPTON (per **I. Croudace**, BSc, PhD) Southampton

CO-OPERATING ANALYSTS AND LABORATORIES (cont.)

UK MANUFACTURERS and USERS

ATI ALLVAC LTD. (per M. Blackwell & M. Webster)	Sheffield	LAFARGE CEMENT UK (per Miss N. Egan)	Barry
BRUNNER MOND LTD. (per Ms. D. Boardman)	Northwich	LAFARGE CEMENT UK (per P. Oakley)	Waterhouses
BUXTON LIME INDUSTRIES (per P. Jackson)	Buxton	LONDON & SCANDINAVIAN ANALYTICAL SERVICES (per P. Hurditch & P. Cooper)	Rotherham
CALUMITE LTD. (per Mrs. N. Johnson, MEng, PhD)	Scunthorpe	LONGCLIFFE QUARRIES LTD. (per N. Weedon)	Brassington
CASTLE CEMENT LTD. (per P. Livesey)	Clitheroe	MACAULAY INSTITUTE (per A. Midwood & G. Newman)	Craigiebuckler
CEMEX UK OPERATIONS (per M. Higgins)	Rugby	MORGAN GROUP TECHNOLOGY LTD.	Stourport-on-Severn
CORUS STRIP PRODUCTS, LLANWERN WORKS (per D.G. Crook)	Newport	NICHOLLS COLTON ANALYTICAL. (per J. Gane)	Leicester
CORUS STRIP PRODUCTS, PORT TALBOT WORKS (per Ms. C. Aitchison, M. Allen & D.C. Richards)	PortTalbot	OMYA UK LTD. (per J. Mansell)	North Ferriby
CORUS TECHNICAL SWINDEN LABORATORIES (per Ms. F. Boué-Bigne & P. Collins)	Rotherham	PILKINGTON EUROPEAN TECHNICAL CENTRE (per S. N. Jamieson, MSc, CChem, MRSC)	Lathom
CORUS ENGINEERING STEELS (per P. Rugg)	Rotherham	RMC READYMIX LTD (per A. Hartley).....	Coventry
CORUS TESTING SOLUTIONS (per Miss Y.A. Snowden)	Scunthorpe	ROCKWARE GLASS LTD. (per P. McCluskey)	Knottingly
CORUS TESTING SOLUTIONS (per Mrs. H. Richmond)	Redcar	SANDVIK HARD MATERIALS (per M.J. Carpenter, BSc)	Coventry
CORUS TESTING SOLUTIONS (TEESSIDE) (per Dr. A.O. Ogunde)	Middlesbrough	SCIENTIFIC ANALYSIS LABORATORIES (per P. Harrington)	Manchester
ELEMENTIS CHROMIUM (per Ms. L. Raybould)	Stockton-on-Tees	SIBELCO MINERALS & CHEMICALS LTD.	Stoke-on-Trent
EUROFINS LABORATORIES (per A. Scott)	Wolverhampton	SIBELCO UK (per Ms. T. Moran)	Whiston
FIRTH RIXSON PLC (per Ms. J. Parker & N. Wrathall)	Glossop	ST. GOBAIN GLASS UK LTD. (per Ms. E. Baguley & I. Anderson)	Eggborough
HOWMET LTD. (per E.J. Farley)	Exeter	STL MIDLANDS (per J. Noonan)	Coventry
INCOTEST (per P. Scrimshire, BSc)	Hereford	VESUVIUS UK LTD. (per P. Bond)	Barlborough

CO-OPERATING ANALYSTS AND LABORATORIES (cont.)

Overseas Laboratories Participating in the Analysis of BAS Certified Reference Materials

AUSTRALIA

QUEENSLAND MAGNESIA (OPERATIONS) PTY LTD Parkhurst
 STANDARD & REFERENCE LABORATORIES Malaga
 WESTERN AUSTRALIAN SPECIALITY ALLOYS Canning Vale

AUSTRIA

BÖHLER EDELSTAHL GmbH & Co. KG Kapfenberg
 TREIBACHER INDUSTRIE AG Treibach-Althofen
 VOESTALPINE STAHL GmbH Donawitz
 VOESTALPINE STAHL GmbH Linz

BELGIUM

AGC FLAT GLASS EUROPE Jumet
 CARSID Couillet
 INISMA Mons
 NYRSTAR Overpelt
 SIDMAR NV Gent
 UMICORE PRECIOUS METALS REFINING Hoboken

BRAZIL

MINERACAO MARACA IND e COM S/A Golas

CANADA

GEOSCIENCE LABORATORIES Ontario
 VALE INCO LTD Copper Cliff
 VALE INCO LTD Thompson
 VALE INCO LTD Port Colborne
 VALE INCO TECHNICAL SERVICES LTD Mississauga

CHILE

ALFRED H. KNIGHT CHILE LTDA Santiago

CZECH REPUBLIC

CALUMITE s.r.o. Ostrava
 GLASS INSTITUTE Králové

DENMARK

FORCE INSTITUTTET Copenhagen

FINLAND

RAUTARUUKKI OY Raahe

FRANCE

ACIERIES DES ANCIZES - AUBERT ET DUVAL Les Ancizes
 ARCELORMITTAL RESEARCH - GROUPE ARCELOR (IRSID) Maizières-les-Metz

ARCELORMITTAL ATLANTIQUE ET LORRAINE Dunkerque
 ARCELORMITTAL FLORANGE Florange
 ARCELORMITTAL FOS-SUR-MER Fos-sur-Mer
 ARCELORMITTAL INDUSTRIEEL CREUSOT Le Creusot
 ASCOMETAL USINE DE FOS Fos
 BUREAU VERITAS LABS Belfort
 CEP INDUSTRIES St Ouen l'Aumone
 CERMEP Grenoble
 CNRS Vemaison
 CORNING Avon
 CTIF Sèvres
 CTIF Charleville
 ST GOBAIN ISOVER Isover
 ST GOBAIN RECHERCHE Aubervilliers
 UGINE et ALZ - GROUPE ARCELOR Isbergues
 UGITECH Ugine
 UNIMETAL - ISPAT Amneville
 USI GROUPE ARCELOR Imphy

GERMANY

AG DER DILLINGER HÜTTENWERKE Dillingen/Saar
 ARCELOR MITTAL BREMEN GmbH Bremen
 BAM BUNDESANSTALT FÜR MATERIALFORSCHUNG UND - PRÜFUNG Berlin
 DEUTSCHE EDELSTAHLWERKE GmbH Siegen
 DEUTSCHE EDELSTAHLWERKE GmbH Witten
 FQZ BRANDENBURG GmbH Eisenhüttenstadt
 GEOFORSCHUNGSZENTRUM POTSDAM Potsdam
 GFE FREMAT GmbH Freiberg
 HÜTTENWERKE KRUPP MANNESMANN GmbH Duisburg
 IFG INSTITUT FÜR GIESSEREITECHNIK Düsseldorf
 KENNAMETAL HERTEL AG Mistelgau
 MAX-PLANCK INSTITUT FÜR EISENFORSCHUNG GmbH Düsseldorf
 METALEUROP WESER BLEI GmbH Nordenham
 MULDENHÜTTEN RECYCLING u. UMWELTECHNIK GmbH Freiberg
 RECYLEX HARZ-METALL GmbH Goslar
 SAARSTAHL AG Völklingen-Saar
 ST GOBAIN DEUTSCHLAND Herzogenrath
 SCHOTT GLAS Mainz
 STAHLINSTITUT VDEh Düsseldorf
 H.C. STARCK GmbH & CO. KG, WERK GOSLAR Goslar
 THYSSENKRUPP NIROSTA GmbH Krefeld
 THYSSENKRUPP STEEL AG Duisburg
 THYSSENKRUPP VDM GmbH Werdohl
 WESER-METALL GmbH Nordenham

CO-OPERATING ANALYSTS AND LABORATORIES (cont.)

Overseas Laboratories Participating in the Analysis of BAS Certified Reference Materials (cont.)

GREECE
 AGRICULTURAL RESEARCH & ANALYTICAL LABORATORIES Athens

INDIA
 CSIR Orissa
 RAGHAVENDRA SPECTRO METALLURGICAL LABORATORY Bangalore

ITALY
 SASSUOLOLAB s.r.l. Sassuolo
 STAZIONE SPERIMENTALE DEL VETRO Murano
 THYSSEN KRUPP ACCIAI SPECIALI TERNI Terni

JAPAN
 NIPPON SHEET GLASS Hyogo

LUXEMBOURG
 CERATIZIT Mamer
 LUXCONTROL S.A. Esch sur Alzette

MALAYSIA
 CERAMIC RESEARCH CO. SDN BHD Selangor

MEXICO
 ALFRED H. KNIGHT DE MEXICO SA de CV Colima

THE NETHERLANDS
 CORUS STAAL BV IJmuiden
 LABORATORY SERVICES INTERNATIONAL BV Rotterdam
 NEDMAG INDUSTRIES Veendam
 NYRSTAR Budel-Dorplein
 PHILIPS RESEARCH EUROPE Eindhoven
 SGS NEDERLAND BV Spijkennisse

NORWAY
 NORTH CAPE MINERALS Lillesand

PERU
 ALFRED H. KNIGHT DEL PERU Lima
 INSPECTORATE SERVICES PERU SAC Callao

SOUTH AFRICA
 PFG BUILDING GLASS (PTY) LTD. Springs

SPAIN
 ACERALIA - GRUPO ARCELOR. Gijon
 ACERINOX, S.A. Algeciras
 CENTRO NACIONAL DE INVESTIGACIONES METALURGICAS (CENIM) Madrid

SWEDEN
 AB SANDVIK COROMANT Stockholm
 BOLIDEN MINERAL AB Skelleftehamn
 GLASFORSKNINGSINSTITUTET Vaxjo
 GUSTAVSSON CONSULTING Stockholm
 HÖGANÄS AB Höganäs
 JERNKONTORET Stockholm
 KANTHAL AB Hallstahammar
 LUOSSAVAARA KIIRUNAVAARA AB (LKAB) Kiruna
 LUOSSAVAARA KIIRUNAVAARA AB (LKAB) Malmberget
 OUTOKUMPU STAINLESS AB Avesta
 OVAKO STEEL AB Hofors
 SANDVIK MATERIALS TECHNOLOGY Sandviken
 SANDVIK TOOLING Stockholm
 SECO TOOLS AB Fagersta
 SGAB ANALYTICA Lulea
 SSAB OXELOSUND AB Oxelosund
 SWEREA KIMAB AB Stockholm
 UDDEHOLM TOOLING AB Hagfors
 UPPSALA UNIVERSITY Uppsala
 YN NILAB AS Avesta

THAILAND
 DEPARTMENT OF SCIENCE SERVICE, MINISTRY OF SCIENCE & TECHNOLOGY Bangkok

TURKEY
 TURKIYE SIS EVE CAM FABRIKALARI A.S. Istanbul

USA
 ALCAN PACKAGING, INC Millville
 ALFRED H. KNIGHT NORTH AMERICA LTD Spartanburg
 ATI ALLVAC Monroe
 CARPENTER TECHNOLOGIES Reading
 GUARDIAN INDUSTRIES CORPORATION Michigan
 NSL ANALYTICAL SERVICES, INC Cleveland
 PCC AIRFOILS LTD Minerva
 SMC HUNTINGDON ALLOYS Huntingdon
 WASHINGTON STATE UNIVERSITY Pullman

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - High Purity Irons and Unalloyed Steels

The figures are listed primarily as a guide to purchasers. In some cases provisional figures are given which may differ slightly from those given on the Certificate. **Always consult the Certificate issued with the sample to obtain the accurate analysis.**

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

High Purity Irons (Finely divided material - units of 100g: 097-1 also available as 38mm dia. x 30, 25 or 3mm discs - see page 17)

ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu	N
088-2	High Purity Iron	0.0006	0.0052	0.0809	0.0048	0.0070	0.0244	<i>0.0025</i>	0.0275	<i>0.0005</i>	0.0061	0.0163	<i>0.001</i>
097-1(C)	High Purity Iron	<i><0.0005</i>	<i><0.01</i>	0.0064	0.0016	0.0022	0.0016	<i><0.001</i>	0.0025	...	0.0051	0.0003	0.0037	0.0020	0.0007

ECRM No.	Description	Nb	Pb	Sn	Ti	V	W	Zr	Bi	Ca	Mg	O	Sb	Ta	Zn
088-2	High Purity Iron (cont)	0.00029	0.00072
097-1(C)	High Purity Iron (cont)	<i><0.001</i>	<i><0.0005</i>	<i><0.0025</i>	<i><0.0015</i>	<i><0.001</i>	<i>≤0.001</i>	<i><0.001</i>	<i><0.0005</i>	<i><0.0005</i>	<i><0.0005</i>	<i>0.05</i>	<i>≤0.001</i>	<i><0.0005</i>	<i><0.0001</i>

Unalloyed Steels (Finely divided material - units of 100g; 111 & 056-2 also available as 44mm dia. x 19 or 50mm discs/057-2, 058-2, 059-2, 064-1, 084-1, 085-1, 086-1, 090-1 and 096-2 also available as 38mm dia. x 30 or 25mm discs - see page 17)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol)	Al (Total)	As	Co	Cu	N	Nb	Pb	Sn	Ti	V	Sb	Ca	Zn
111	...	Low Carbon Steel	0.0258	0.0253	0.155	0.0033	0.0054	0.0197	0.0008	0.0387	...	0.0348	0.0017	0.0144	0.0171	0.0034	<i>0.0005</i>	<i><0.001</i>	0.0015	0.0004	0.0009	<i><0.001</i>	<i><0.0005</i>	...
159/3	055-1	0.5% Carbon Steel	0.51	0.24	0.77	0.016	0.036	<i>0.16</i>	<i>0.02</i>	<i>0.12</i>	<i>0.15</i>
161/4	...	0.8% Carbon Steel	0.817	0.202	0.504	0.0105	0.0096
163/2	063-1	1.2% Carbon Steel	1.26	0.24	0.30	0.019	0.022	<i>0.16</i>	<i>0.012</i>	<i>0.10</i>	<i>0.02</i>	...	<i>0.09</i>	<i>0.005</i>
232/2	051-1	0.1% Sulphur Steel	0.181	<i>0.11</i>	1.18	<i>0.025</i>	0.126	<i>0.05</i>	...	<i>0.14</i>	<i>0.15</i>
237/2	060-1	0.1% Carbon Steel	0.122	<i>0.17</i>	0.45	<i>0.024</i>	<i>0.031</i>	<i>0.028</i>	<i><0.005</i>	<i>0.039</i>	...	<i>0.004</i>	<i>0.060</i>	0.0040	<i>0.005</i>
238/2	061-1	0.2% Carbon Steel	0.210	0.12	<i>0.61</i>	<i>0.019</i>	<i>0.034</i>	<i>0.21</i>	<i>0.10</i>
270	054-1	0.09% Phosphorus Steel	0.22	<i>0.05</i>	<i>0.88</i>	0.092	<i>0.10</i>	<i>0.17</i>	<i>0.02</i>	<i>0.14</i>	<i>0.03</i>	...	<i>0.21</i>	<i><0.01</i>
...	056-2(C)	0.8% Carbon Steel	0.8181	0.2006	0.5073	0.0103	0.0093	0.0146	...	0.0218	0.00024	<i><0.001</i>	0.0129
...	057-2(C)	0.05% Carbon Steel	0.0507	<i>0.003</i>	0.246	0.0120	0.0127	0.0114	...	0.0096	<i>0.055</i>	0.059	0.0146	0.00230
...	058-2(C)	0.15% Sulphur Steel	0.424	0.1080	1.186	0.0098	0.1712	0.1211	0.0589	0.199	0.0095	...	0.261	0.0107
...	059-2(C)	0.7% Carbon Steel	0.721	0.188	0.495	0.0046	0.0084	0.0090	0.0018	0.0198	0.00020	0.00045	0.0074	0.0051
...	064-1(C)	Nb/Ti Interstitial Free Steel	0.0026	0.0065	0.1641	0.0091	0.0104	0.0184	0.00077	0.0115	0.0302	0.0330	0.0036	0.0027	0.0077	0.0026	0.0146	0.00018	0.00051	0.0189	0.00015
...	084-1(C)	0.4% Carbon Steel	0.391	0.265	0.860	0.018	0.029	...	0.033	0.154	0.267	0.023
...	085-1(C)	0.3% Sulphur Steel	0.067	0.008	0.977	0.062	0.336	0.019	0.291	0.0010	0.0021	0.0073	...	0.0025
...	086-1(C)	0.3% Carbon Steel	0.297	0.206	0.879	0.0238	0.0371	0.150	...	0.168	0.0230	...	0.320	0.0263
...	087-1(C)	0.15% Carbon Steel	0.1740	0.2631	0.6711	0.0103	0.0461	0.0781	0.0206	0.1177	0.0243	0.0148	0.1707	0.0171	0.0046
...	090-1(C)	1% Carbon Steel	1.054	0.281	0.226	0.0128	0.0095	0.121	0.0089	0.053	0.0146	0.00043	0.00239	0.204	0.00090	...	0.00209
...	091-1	0.5% Carbon Steel	0.518	0.312	0.098	0.310	0.0111
...	096-1(C)	Low S, Low Ca Steel	0.113	0.263	1.35	0.019	0.0009	0.019	0.003	0.020	0.040	0.044	<i>0.005</i>	<i>0.006</i>	0.022	...	0.029	<i>0.0004</i>	<i>0.005</i>	...	0.0036	<i>0.001</i>	0.0021	...
...	096-2(C)	Low S, Ca-Treated Steel	0.1050	0.262	1.320	0.0128	0.0016	0.0243	0.0020	0.0253	...	0.0460	0.0170	...	0.0252	0.0020	...

Unalloyed Steels (Continued)

BCS-CRM No.	ECRM No.	Description	Bi	Cd	Ga	Hg	Se	Te	Tl
...	090-1(C)	1% Carbon Steel	<i><0.00002</i>	<i><0.00002</i>	0.00228	<i><0.00001</i>	<i><0.0002</i>	<i><0.0002</i>	<i><0.0001</i>

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Unalloyed Steels and High Speed Tool Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Unalloyed Steels (cont.) (Finely divided material - units of 100g; 431/2-435/2, 453/1 & 456/2-460/2, also available as 38mm dia. x 19mm discs - see page 17)

BCS-CRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol)	Al (Total)	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	W	Zr	Sb
431/2	Plain Carbon Steels	0.0249	0.015	0.902	0.121	0.0065	0.049	<i>0.004</i>	0.040	...	<i>0.01</i>	<i>0.005</i>	...	<i>0.006</i>	<i>0.015</i>	0.0052	0.0040	...	< <i>0.001</i>	<i>0.005</i>	<i>0.003</i>	<i>0.004</i>
432/2		0.0065	0.0822	0.712	0.0171	0.036	0.0166	<i>0.002</i>	0.0196	...	< <i>0.002</i>	<i>0.006</i>	<i>0.015</i>	0.0066	0.0174	< <i>0.001</i>	<i>0.003</i>
433/2		0.096	0.0071	1.188	0.011	0.0083	0.0262	<i>0.004</i>	0.037	<i>0.006</i>	<i>0.025</i>	...	0.0590	<i>0.001</i>	<i>0.003</i>
434/2		0.275	0.510	1.546	0.0611	0.0141	0.238	<i>0.014</i>	0.037	<i>0.006</i>	<i>0.025</i>	0.0104	0.038	<i>0.04</i>	<i>0.04</i>
435/2		0.489	0.328	0.390	0.0373	0.0424	0.184	<i>0.018</i>	0.133	0.0116	<i>0.05</i>	...	0.134	<i>0.005</i>	<i>0.015</i>
451/1	Carbon Steel	0.051	0.116	0.62	0.009	0.014	0.104	0.039	0.016	0.041	0.47	<i>0.0005</i>	0.002	0.105	...	0.099
452/1	Residual Series (Group A)	0.323	0.055	1.30	0.035	0.017	0.067	0.054	0.19	0.015	0.22	<i>0.0002</i>	0.094	0.031	...	0.054
453/1		0.160	0.34	1.38	0.044	0.026	0.26	0.081	0.11	0.052	0.099	<i>0.0001</i>	0.022	0.073	...	0.30
456/2	Carbon Steel Residual Series (Group B)	0.112	0.297	0.220	0.0212	0.0221	< <i>0.002</i>	0.0018	...	0.0015	0.0504	0.0057	0.0189	0.0221	...	<i>0.013</i>	0.0172
457/2		0.307	0.105	0.327	0.0098	0.0448	0.082	0.087	...	0.0046	0.0217	0.0174	0.0098	0.153	...	0.025	0.050
458/2		0.198	0.504	0.479	0.0281	0.0314	0.052	0.055	...	0.0069	0.198	0.0510	0.0140	0.105	...	<i>0.062</i>	0.089
459/2		0.467	0.640	0.909	0.0482	0.0481	0.0134	0.0154	...	0.0110	0.0890	0.0102	0.0044	0.0585	...	0.074	0.0121
460/2		0.383	0.126	0.616	0.0374	0.0099	0.0193	0.0240	...	0.0027	0.0106	0.068	0.0005	0.0322	...	< <i>0.0005</i>	0.0006

Unalloyed Steels (cont.) (Rod material - BCS-CRM 318A is a pair of 6.35mm dia. x 95mm rods, BCS-CRM 318B is a single 12.7mm dia. x 127mm rod)

BCS-CRM No.	Description	Form	C	Si	Mn	P	S	Al	O
318A	0.01% Oxygen Steel	6.35mm dia. x 95mm rod	<i>0.083</i>	<i>0.12</i>	<i>0.39</i>	<i>0.018</i>	<i>0.035</i>	< <i>0.002</i>	0.0096
318B	0.01% Oxygen Steel	12.7mm dia. x 127mm rod	<i>0.083</i>	<i>0.12</i>	<i>0.39</i>	<i>0.018</i>	<i>0.035</i>	< <i>0.002</i>	0.0103

High Speed Tool Steels (Finely divided material - units of 100g; 483/1 also available in disc form for spectroscopic analysis - see page 20)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Co	Cu	Sn	V	W	
220/2	254-1	High Speed Tool Steels	0.88	0.19	0.30	0.023	0.029	5.12	4.92	0.12	0.32	0.09	0.019	1.94	6.97	
241/2	251-1		0.84	0.21	0.27	0.024	0.025	5.35	0.53	0.15	<i>0.009</i>	5.70	0.08	0.025	1.59	19.9
481	...		0.69	0.14	0.29	0.021	0.027	3.56	0.22	0.21	0.52	14.2
482	...		0.70	0.13	0.28	0.021	0.025	4.09	0.27	0.24	0.98	18.1
483	...		0.67	0.11	0.29	0.019	0.025	3.21	0.17	1.94	0.54	10.8
484	...		0.85	0.20	0.21	0.030	0.024	5.17	1.07	10.2	0.93	22.4

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Alloy Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Alloy Steels (Finely divided material - units of 100g; 112-114 also available as 44mm dia. x 19 or 50mm discs; 186-1, 195-1, 404/1, 401/2-410/2 & 421-424 also available in disc form for spectroscopic analysis - see page 18)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	W	Zr	Ca	Sb	Zn	
112	...	Low Alloy Steel	0.394	0.289	0.436	0.0043	0.0026	1.236	0.190	1.461	0.0148	0.0021	0.0007	0.0175	0.149	0.0024	0.0065	<i><0.001</i>	0.0086	0.0100	0.0088	...	<i><0.001</i>	<i><0.0005</i>	<i><0.001</i>	...	
113	...	Low Alloy Steel	0.837	0.931	1.207	0.0595	0.0294	1.248	0.056	0.0784	0.0151	0.0020	0.0066	0.0415	0.179	0.0109	0.0487	<i><0.001</i>	0.0067	0.0390	0.201	0.012	0.0029	<i><0.001</i>	<i><0.003</i>	...	
114	...	Low Alloy Steel	0.403	0.295	0.416	0.0044	0.0046	0.187	0.184	1.502	0.078	0.0025	0.0008	0.0171	0.360	0.0043	0.0042	<i><0.001</i>	0.041	0.0096	0.0086	<i><0.001</i>	0.0051	<i><0.001</i>	<i><0.0025</i>	...	
214/2	152-1	Mn-Mo Steel	0.39	0.18	1.61	0.032	0.043	0.09	0.26	0.15	0.21	<i><0.01</i>	
219/4	153-1	Ni-Cr-Mo Steel	0.314	0.079	0.81	0.011	0.027	0.66	0.58	2.55	<i>0.003</i>	0.088	0.011	
222/1	154-1	Ni Steel	<i>0.31</i>	<i>0.22</i>	<i>0.62</i>	<i>0.020</i>	<i>0.009</i>	<i>0.05</i>	<i>0.029</i>	3.54	<i>0.038</i>	<i>0.14</i>	
225/2	155-1	Ni-Cr-Mo Steel	0.40	0.23	0.56	0.019	0.012	1.08	0.34	1.43	<i>0.01</i>	<i>0.04</i>	<i>0.007</i>	<i>0.02</i>	<i>0.17</i>	<i>0.012</i>	<i>0.003</i>	...	<i>0.02</i>	...	<i><0.01</i>	...	<i><0.01</i>	...	<i>0.006</i>	...	
317	151-1	Low C, High Si Steel	0.028	3.49	0.085	0.015	0.023	
...	186-1(C)	Silico Manganese Steel	0.6104	1.719	0.870	0.0223	0.0354	0.218	0.0482	0.190	0.0143	0.281	
...	195-1(C)	Cr-Mo-Ni Steel	0.756	0.466	0.571	0.0160	0.0121	1.566	0.768	0.327	0.0355	0.0100	...	0.0010	<i>0.002</i>	...	0.312	0.0017	<i>0.0008</i>	0.0046	
405	...	Low Alloy Steels	0.058	1.38	1.28	0.017	0.060	0.21	0.017	0.12	0.015	0.32	
408	...		0.28	0.24	0.64	0.043	0.030	0.090	0.14	4.58	0.73	0.063	
404/1	...	Low Alloy Steels	0.74	0.87	0.31	0.057	0.024	0.48	0.31	0.40	0.34	0.11	
405/1	...		0.032	1.71	1.28	0.018	0.069	0.15	0.002	0.22	0.013	0.28
407/1	...		0.47	0.59	0.047	0.030	0.010	2.95	0.78	0.59	0.57	0.18
408/1	...		0.285	0.23	0.51	0.037	0.028	0.102	0.09	4.45	0.66	0.031
409/1	...		0.082	1.46	0.44	0.025	0.021	0.94	0.65	3.06	0.014	0.048	0.09
401/2	...	Low Alloy Steels	0.935	0.602	1.197	0.0265	0.0078	0.138	0.495	0.019	0.074	0.0042	0.101	<i>0.015</i>	0.496	
402/2	...		1.311	0.111	0.228	0.0161	0.0138	0.652	0.140	0.808	0.161	0.302	0.0069	0.194
403/2	...		0.750	0.209	1.677	0.055	0.0381	0.463	0.088	0.223	0.0485	0.221	<i>0.010</i>	0.341
404/2	...		0.696	1.121	0.532	0.0479	0.0228	0.774	0.307	0.393	0.017	0.427	0.0089	0.107
405/2	...		0.044	0.947	0.903	0.0095	0.058	0.206	0.025	0.102	0.330	<i>0.009</i>	0.022	<i>0.011</i>	0.411
406/2	...		0.173	0.342	0.447	0.0102	0.043	2.001	0.98	1.62	0.013	0.012	<i>0.006</i>	0.289	<i>0.009</i>	...	0.0002	<i>0.001</i>	...	0.010
407/2	...		0.490	0.66	0.195	0.038	0.0105	3.03	0.83	0.527	0.040	0.0068	0.397	<i>0.011</i>	0.19
408/2	...		0.289	0.237	0.557	0.056	0.030	0.111	0.098	4.13	0.154	0.0046	0.694	0.0075	...	0.0006	<i>0.002</i>	...	0.067
409/2	...		0.086	1.18	0.559	0.0141	0.0179	1.318	0.599	3.02	0.094	0.205	0.0108	0.008
410/2	...		0.428	1.10	0.419	0.074	0.041	1.684	0.432	2.07	0.046	0.0053	0.0248	0.436	0.0155	0.44
421	...	Low Tungsten Steels	<i>0.049</i>	<i>0.07</i>	<i>0.11</i>	<i>0.012</i>	<i>0.027</i>	...	<i>0.028</i>	<i><0.02</i>	0.52	
422	...		<i>0.036</i>	<i>0.06</i>	<i>0.09</i>	<i>0.015</i>	<i>0.025</i>	...	<i>0.033</i>	<i><0.02</i>	1.28
423	...		<i>0.030</i>	<i>0.05</i>	<i>0.07</i>	<i>0.017</i>	<i>0.027</i>	...	<i>0.027</i>	<i><0.02</i>	2.06
424	...		<i>0.024</i>	<i>0.05</i>	<i>0.09</i>	<i>0.02</i>	<i>0.024</i>	...	<i>0.036</i>	<i><0.02</i>	3.02

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Highly Alloyed Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Highly Alloyed Steels (Finely divided material - units of 100g; 272-1, 276-2, 285-2, 287-1, 292-1, 295-1, 296-1, 340 (SS70), 461/1-468/1, 466/2, 469-473, 475 also available in disc form for spectroscopic analysis - see pages 19 & 20)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	Mg	Sb	Others
...	272-1(C)	12% Chromium Steel	0.2815	0.420	0.600	0.0156	0.0197	11.927	0.0030	0.244	0.0046	0.0116	0.0018	0.0145	0.0192	0.0508	0.0028	<i>0.0004</i>	<i>0.0008</i>	0.00096	0.0167	<i>0.0002</i>	0.0007	0.00090 Ca 0.0031 Zn
...	276-2(C)	5% Cr-Mo-V Steel	0.399	1.034	0.365	0.0093	0.0189	4.975	1.134	0.203	0.183	0.0116	0.0133	...	0.296
...	281-1	18/9 Stainless Steel & Ti	0.048	0.929	0.786	0.012	0.016	18.17	...	9.37	0.015	<i>0.015</i>	0.0012	0.023	0.076	0.023	...	0.0005	0.009	0.216
...	285-2(C)	Maraging Steel	0.0018	0.0117	0.0168	0.0053	0.0025	0.0236	4.99	18.07	0.1067	7.76	0.0094	0.0007	...	<i>0.001</i>	0.520	0.0050 Zr
...	287-1(C)	High B Stainless Steel	0.0164	0.569	1.478	0.0267	0.0014	18.61	0.247	10.35	0.924	0.148	0.203	0.0194
...	292-1(C)	Nb-Stabilised Stainless Steel	0.0367	0.402	1.744	0.0175	0.0055	18.00	0.0464	10.09	<i>0.002</i>	<i>0.008</i>	<i>0.0003</i>	0.0255	0.0391	0.0640	0.571	<i>0.001 Ta</i>
...	295-1(C)	4% Mo-Cr-Ni Steel	0.0166	0.418	1.758	0.0167	0.0003	19.51	3.996	24.40	0.0203	0.0041	0.0018	0.0450	1.481	0.0615	0.0025	...	0.0456	<i>0.0003</i>	0.0007	48.36 Fe
...	296-1(C)	Jethete Steel	0.1166	0.242	0.676	0.0178	0.0026	11.82	1.700	2.790	0.0275	0.0139	<i>0.0003</i>	0.0218	0.1498	0.0214	...	0.00016	0.0131	...	0.363
332	...	Austenitic Stainless Steel	0.063	0.44	0.80	0.015	0.020	12.80	...	12.45	<i>0.037</i>	<i>0.10</i>	<i>0.02</i>
339	...	Ferritic Stainless Steels	0.29	0.36	0.41	0.022	0.022	12.40	...	0.37	<i>0.08</i>
340	...		0.18	0.35	0.38	0.024	0.020	16.35	...	0.40	<i>0.06</i>
341	...		0.100	0.31	0.43	0.016	0.024	24.00	...	0.56	<i>0.10</i>
342	...		0.18	0.92	0.91	0.030	0.026	16.15	0.69	2.16	<i>0.08</i>
462	...	Austenitic Stainless Steels	0.092	0.46	0.74	0.010	0.018	12.35	...	12.55	...	0.007	0.0005
463	...		0.088	0.51	0.77	0.015	0.017	18.30	...	9.65	<i>0.0004</i>
461/1	...		0.0103	0.374	0.686	0.0053	0.0051	14.727	0.0138	6.124	<i>0.002</i>	<i>0.004</i>	...	<i>0.004</i>	0.0091	<i>0.005</i>
462/1	...		0.0345	0.463	0.722	0.0053	0.0041	11.888	0.0304	12.85	0.0112
463/1	...		0.019	0.270	1.400	0.025	0.019	18.46	0.265	10.20	0.0022	0.116	0.276	0.063	<i><0.005</i>	<i>0.04</i>
464/1	...		0.086	0.57	0.791	0.020	0.028	25.39	...	20.05	...	<i>0.003</i>	...	0.054	0.0004
465/1	...		0.066	0.405	1.380	0.021	0.012	17.31	0.092	9.24	0.026	...	0.0006	0.053	0.098	0.010	...	<i><0.001</i>	...	0.40	0.102
466/2	...		0.0141	0.480	1.311	0.0105	0.0069	17.84	2.776	10.20	<i>0.002</i>	0.0020	0.0039	0.0184	0.0278	0.0508	<i>0.001</i>	<i><0.0001</i>	<i><0.001</i>	<i>0.002</i>	0.0346
467/1	...		0.082	0.52	0.788	0.018	0.019	18.09	...	9.21	...	0.004	0.99	0.004	0.0017 Ta
468/1	...		0.143	1.41	1.70	0.014	0.020	17.96	...	8.90	0.018
469	...	Ferritic Stainless Steels	0.279	0.421	0.598	0.015	0.020	11.93	...	0.246	<i>0.01</i>	<i>0.02</i>	<i>0.02</i>
470	...		0.153	0.335	0.235	0.024	0.035	17.68	...	0.369	<i>0.02</i>	<i>0.02</i>	<i>0.02</i>
471	...		0.095	0.326	0.417	0.018	0.023	23.85	...	0.96	<i>0.02</i>	<i>0.02</i>	<i>0.03</i>
472	...		0.227	1.05	1.02	0.032	0.029	15.82	0.661	1.95	<i>0.02</i>	<i>0.02</i>	<i>0.02</i>
473	...		0.172	0.604	0.494	0.019	0.030	9.06	0.95	<i>0.06</i>	<i>0.01</i>	<i>0.03</i>	<i>0.02</i>
474	...	Stainless Steels	0.022	0.17	1.70	0.008	0.020	19.06	3.55	14.74	<i>0.006</i>	0.030	...	<i>0.02</i>	0.35	0.30
475	...		0.050	0.21	0.89	0.037	0.008	14.14	1.59	5.66	0.013	0.22	1.94	...	0.22	...	0.015
290/2	253-1	High Manganese Steels	1.15	0.34	12.5	0.042	0.019	0.16	<i>0.031</i>	0.29	<i>0.35</i>	<i>0.17</i>	<i>0.013</i>	<i>0.02</i>	
491	...		0.92	0.90	16.1	0.026	0.012	1.45	0.60	0.05	0.042	<i>0.04</i>	<i>0.06</i>
494	...		1.24	0.26	13.55	0.040	0.005	0.56	0.079	0.69	0.004	<i>0.43</i>	<i>0.19</i>	<i>0.02</i>
495	...		0.82	0.46	13.6	0.036	0.014	1.93	0.035	1.05	0.103	<i>0.09</i>	<i>0.02</i>
495/1	...		0.81	0.58	13.1	0.054	0.026	1.93	0.11	1.13	0.17	<i>0.02</i>

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Special Alloys, Cast Irons and Ferro-Alloys

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Special Alloys (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	S	Ni	Al	Co	Cu	Nb	Ti	Ta
383	...	Alcomax III	0.025	...	<i>0.07</i>	0.20	<i>13.2</i>	<i>7.7</i>	<i>24.4</i>	<i>2.63</i>	<i>0.51</i>
398	...	Alnico HC	0.025	0.11	0.065	0.19	16.59	9.98	14.92	6.09	0.13	0.765	...
...	376-1	24% Cobalt Magnet Alloy	0.0256	0.313	0.046	0.0040	13.37	8.12	23.70	2.94	0.309	0.158	<i>0.016</i>

Cast Irons (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C	Graphite	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Cu	N	Sn	Ti	V	Mg
...	451-2	Austenitic Cast Iron	2.059	...	2.092	1.079	0.0593	0.0315	1.097	...	14.01	6.26
206/3	453-1	High Si and P Iron	<i>2.44</i>	<i>2.37</i>	3.17	0.72	1.63	0.049	0.053	...	0.068	...	0.019	0.10	<i>0.040</i>	0.050	...
236/3	454-1	Hematite Iron	<i>2.53</i>	<i>1.96</i>	2.00	1.16	0.046	0.068	<i>0.21</i>	...	<i>0.025</i>	<i>0.07</i>	0.052
...	481-1	Nodular Iron	3.907	...	2.288	0.448	0.0192	0.0040	0.063	0.0110	1.190	0.0229	0.0096	0.150	0.0507
...	482-2	Low Alloy Cast Iron	2.599	...	1.815	0.728	0.0974	0.0491	0.675	0.454	2.284	1.231
...	483-1	High Duty Iron	2.463	1.65	1.755	0.596	0.615	0.103	0.039	0.130
...	484-1	Whiteheart Malleable Iron	3.203	...	0.717	0.395	0.121	0.230	0.155
...	486-1	Foundry Iron	2.212	...	2.429	0.841	0.996	0.0233	0.104	...	0.0571	0.548	...	0.074	...	0.0197	...
...	489-1	White Iron	2.860	...	1.524	<i>0.510</i>	0.815	0.155	0.274	<i>0.0056</i>

Ferro-Alloys (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol)	Al (Total)	B	Co	Cu	N	Nb	Sn	Ti	V	W	Ta	Fe
242/2	555-1	Ferro-Tungsten	0.025	1.75	...	<i>0.02</i>	<i>0.018</i>	0.14	0.034	79.9	...	<i>15.2</i>
...	576-1	Ferro-Niobium (40% Nb)	0.201	1.79	2.53	43.90	0.195	1.32	0.306	...
...	577-1	Ferro-Vanadium	0.089	1.79	0.158	0.035	0.034	0.053	<i>0.21</i>	0.414	0.054	50.16
...	578-1	Ferro-Molybdenum	0.016	0.208	...	0.024	0.065	...	72.23	0.136
...	579-1	Ferro-Niobium (60% Nb)	0.037	1.03	...	0.064	0.021	1.86	...	0.0051	62.87	0.344	0.567	3.85	...
...	580-1	Low C Ferro-Chromium	0.019	0.306	...	0.011	...	72.18	0.047	...	0.035	0.083
...	583-1	Ferro-Manganese	0.333	0.396	86.42	0.146	<i>0.007</i>	<i>0.041</i>	<i>12.3</i>
...	584-1	Ferro-Titanium	0.044	1.80	1.13	0.032	0.030	<i>6.0</i>	7.19	37.17
...	585-2	High C Ferro-Chromium	5.488	4.69	0.801	0.0255	0.0320	49.05	...	0.294	0.062	...	0.0127	0.263	0.282	38.67
...	587-1	Ferro-Boron	0.738	<i>0.129</i>	0.272	<i>0.020</i>	<i>0.001</i>	<i>0.10</i>	<i>0.005</i>	0.047	18.7	<i>0.010</i>	<i>0.04</i>	<i>0.004</i>
...	590-1	Ferro-Tungsten	0.0250	1.05	0.136	...	<i>0.07</i>	...	0.101	<i>0.37</i>	0.0484	0.045	79.55	...	<i>17.9</i>

BRITISH CHEMICAL STANDARD CERTIFIED REFERENCE MATERIALS - Aluminium, Magnesium & Copper Base Alloys

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Aluminium and Magnesium Base Alloys (Finely divided material - units of 100g)

BCS-CRM No.	Description	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Pb	Sn	Ni	Sb	Zr	Be	Total Rare Earths	Al
181/3	2.5% Cu Aluminium Alloy	0.30	0.72	2.48	1.10	1.57	0.04	2.52	0.058	0.101	...	2.00	Bal.
182/3	11% Si Aluminium Alloy	11.03	0.51	0.037	0.26	0.067	...	0.128	0.107	0.056	0.027	0.046	Bal.
216/3	5% Cu Aluminium Alloy	0.74	0.77	5.45	0.76	0.76	0.108	0.214	0.20	0.052	0.052	0.24	<i>0.01</i>	0.084	Bal.
262/1	10% Mg Aluminium Alloy	0.16	0.20	0.039	0.084	10.75	<i>0.002</i>	0.085	0.005	<i>0.05</i>	<i>0.04</i>	0.071	<i><0.01</i>	...	Bal.
263/2	5% Mg Aluminium Alloy	0.14	0.26	0.019	0.36	4.67	0.074	0.056	0.022	<i><0.001</i>	...	Bal.
268/1	5% Si Aluminium Alloy	5.49	0.47	1.35	0.24	0.49	...	0.028	<i>0.008</i>	0.028	0.031	0.16	Bal.
300/1	6% Zn Aluminium Alloy	0.14	0.24	1.27	0.33	2.74	0.13	5.87	0.09	0.18	Bal.
343	Wrought Aluminium Alloy	0.52	0.39	0.28	0.69	0.70	0.14	0.028	0.024	Bal.
349	3.5% Cu Aluminium Alloy	1.19	0.154	3.40	0.111	0.024	...	0.298	0.034	0.077	0.074	Bal.
380/1	2% Si Aluminium Alloy	1.93	1.24	0.91	0.094	0.24	<i><0.001</i>	0.025	0.024	<i>0.014</i>	...	0.94	Bal.
307	Magnesium Alloy (ZRE 1)	<i><0.001</i>	0.002	0.005	0.006	Bal.	...	2.08	<i><0.001</i>	<i><0.001</i>	...	0.56	...	2.84	<i>0.008</i>
316	8% Al Magnesium Alloy	0.055	0.009	0.040	0.28	Bal.	...	0.68	...	0.024	0.005	0.004	8.01
505	Aluminium-Silicon Alloys	12.8	0.30	0.05	0.52	0.05	...	0.24	0.03	0.09	0.17	0.20	Bal.
506		13.9	0.40	0.02	0.21	0.12	...	0.30	0.07	0.02	0.13	0.13	Bal.

Copper Base Alloys (Finely divided material - units of 100g)

BCS-CRM No.	Description	Cu	Sn	Zn	Pb	P	Ni	Fe	Al	Mn	Sb	As	Si	Bi	Mg	S	C	Cd
179/2	High Tensile Brass (Cast)	58.5	0.70	35.8	0.35	...	0.56	1.02	2.22	0.86	...	<i>0.008</i>	0.044	<i>0.003</i>
180/2	Copper Nickel	68.12	<i>0.003</i>	...	30.35	0.68	...	0.75	<i>0.018</i>	0.006	0.04	...
183/4	Leaded Gunmetal	84.08	7.27	3.47	3.15	0.090	1.30	0.056	<i><0.002</i>	<i>0.01</i>	0.23	0.13	<i>0.01</i>	0.005	...	0.11
207/2	Gunmetal	87.35	9.74	1.60	0.70	<i>0.018</i>	0.28	0.029	0.013	...	0.10	0.066	0.016	0.04
304/1	Copper-Aluminium	80.23	0.03	0.31	0.010	...	4.82	4.64	9.71	0.12	0.08	...	<i><0.01</i>
344	70/30 Brass	68.98	...	30.98
364	Leaded Bronze	80.6	9.35	0.13	9.25	0.056	0.28	<i><0.005</i>	<i><0.002</i>	...	0.18	<i>0.07</i>	<i><0.005</i>	<i><0.01</i>	...	<i>0.06</i>
374	Phosphor Bronze	89.5	9.80	0.006	0.064	0.59	0.014	<i><0.005</i>	<i><0.005</i>	...	<i>0.01</i>	...	<i><0.005</i>	<i>0.007</i>	...	0.012
385	Leaded Brass	58.7	0.27	38.5	2.24	...	0.13	0.15	<i><0.005</i>	<i><0.005</i>	<i><0.01</i>
390	High Tensile Brass (Wrought)	57.1	0.34	38.6	1.04	...	0.033	0.83	0.83	1.30	<i>0.023</i>	<i>0.011</i>
399	Phos. Deoxidised Copper	<i>99.93</i>	<i>0.003</i>	<i>0.003</i>	<i>0.002</i>	0.045	<i>0.002</i>	<i>0.006</i>	<i><0.001</i>	<i><0.001</i>	...	<i>0.001</i>	<i>0.003</i>

BRITISH CHEMICAL STANDARD CERTIFIED REFERENCE MATERIALS - Lead, Tin, Nickel & Titanium Base Alloys, Chromium Metal and Cements

CHEMICAL COMPOSITION - Figures in bold type certified, figures in small italic type only approximate.

Lead and Tin Base Alloys (Finely divided material - units of 100g)

nominal mass content in %

BCS-CRM No.	Description	Pb	Sn	Sb	Cu	As	Bi	Cd	Fe	Ni	Zn	Al	Ag	Au	In
177/2	Lead Base White Metal	84.5	5.07	10.1	0.12	0.05	0.028	0.007	<i>0.008</i>
178/2	Tin Base White Metal	3.18	82.2	9.45	4.58	0.15	0.11	0.14	0.024	0.17	0.040	<i>0.005</i>	<i>0.02</i>
347	Electronic Fluxsolder	Bal.	62.6	0.191	0.169	<i>0.02</i>	0.080	0.0040	<i>0.002</i>	0.0072	0.0015	<i><0.001</i>	0.099	0.037	<i>0.006</i>

Nickel Base Alloys (Finely divided material - units of 100g - 345, 346 (346A), 350, 351, 363/1 & 387/1 also available in disc form for spectroscopic analysis - see page 21)

MAJOR ELEMENTS - nominal mass content in %

BCS-CRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	Nb	Ti	V	W	Zr	Fe	Sb
310/1	Nimonic '90' Alloy	0.068	0.46	0.35	19.45	...	58.6	1.06	...	17.0	2.43	0.25	...
345	IN 100 Alloy	0.153	9.95	3.01	Bal.	5.58	0.019	14.71	4.74	1.00	...	0.044
346	IN 100 Alloy	<i>0.15</i>	<i>10</i>	<i>3</i>	Bal.	<i>5.5</i>	...	<i>15</i>	<i>5</i>	<i>1</i>
350	IN 713 Alloy	0.138	0.110	0.019	13.43	4.29	70.8	5.97	0.013	0.338	...	2.17	0.87	...	0.094	0.072	1.50	...
351	IN 718 Alloy	0.025	0.14	0.037	0.006	0.0006	18.12	3.06	53.1	0.55	0.0051	0.136	0.016	5.20	1.06	18.26	...
363/1	Monel Alloy 400	0.140	0.028	1.26	...	<i>0.002</i>	<i>0.05</i>	...	64.7	0.027	...	0.032	31.90	...	<i>0.03</i>	1.86	...
371	Commercial Nickel	0.30	0.34	0.013	Bal.	0.39
387/1	Nimonic 901 Alloy	0.033	0.06	0.025	0.0033	0.0028	11.35	5.83	41.2	0.24	0.017	0.020	0.0076	<i>0.006</i>	3.00	38.4	0.0003

Nickel Base Alloys (continued)

TRACE ELEMENTS - nominal mass content in µg/g

BCS-CRM No.	Description	Pb	Bi	Ag	Se	Te	Tl	Sb	As	Cd	Ga	Sn	Zn	Mg	Ca	In
345	IN 100 Alloy	0.21	<i><0.2</i>	<i><0.2</i>	<i><0.5</i>	<i><0.2</i>	<i><0.2</i>	<i><2</i>	<i>2</i>	<i><0.1</i>	8.2	5.6	<i><0.5</i>	5.5	<i><5</i>	...
346	IN 100 Alloy	21.0	10.4	35.0	9.1	11.7	1.8	47	50.3	0.42	50.6	91	28.9	147	36	19
371	Commercial Nickel	600

Titanium Base Alloys (Finely divided material - units of 50g)

nominal mass content in %

BCS-CRM No.	Description	Al	V	Fe	Cu	Ni	Cr	Mo	N	Sn	Si	W	C	H	O	B	Zr	Y
356	Titanium Alloy	6.25	4.05	0.124	0.0055	0.0070	0.0112	0.0020	0.0103	<i>0.0155</i>	<i>0.0200</i>	<i>0.0010</i>	<i>0.0085</i>	<i>0.0019</i>	<i>0.2000</i>	<i><0.0005</i>	<i><0.0005</i>	...
357	Titanium Alloy	5.46	3.53	0.202	0.0537	0.0511	0.0521	0.053	0.0148	<i>0.0620</i>	<i>0.0500</i>	<i><0.001</i>	<i>0.0072</i>	<i>0.0012</i>	<i>0.2500</i>	<i>0.0013</i>	<i>0.0455</i>	<i>0.0046</i>

Chromium Metal (Finely divided material - units of 100g)

nominal mass content in %

BCS-CRM No.	Description	C	Si	S	N	Fe	O	Al (Total)
361	Chromium Metal	0.0039	0.0449	0.0043	0.0079	0.092	0.101	<i>0.083</i>

Cements (Finely divided material - units of 100g)

nominal mass content in %

BCS-CRM No.	Description	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	Cr ₂ O ₃	Mn ₂ O ₃	CaO	MgO	Na ₂ O (Acid Sol)	K ₂ O (Acid Sol)	P ₂ O ₅	SO ₃	SrO	Cl
353	Sulphate Resisting Portland Cement	20.5	3.77	0.16	4.82	<i>0.02</i>	0.23	64.8	2.42	0.10	0.49	0.077	2.25	0.23	<i>0.01</i>
354	White Portland Cement	21.8	4.85	<i>0.04</i>	0.30	<i>0.003</i>	0.057	70.0	0.42	0.10	0.11	0.12	2.25	0.11	<i>0.005</i>

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Non-Metallic Materials

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Ores (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	Fe	FeO	SiO ₂	Al ₂ O ₃	Cr ₂ O ₃	TiO ₂	CaO	MgO	S	P	Mn	MnO	Na ₂ O	K ₂ O	CO ₂	As ₂ O ₃	BaO	Pb	L.O.I.
176/2	...	Manganese Ore	6.86	...	2.53	5.2	...	0.30	0.09	0.04	0.018	0.087	47.5	...	0.11	1.30	...	0.22	0.19	<i>0.01</i>	...
301/1	651-1	Lincolnshire Iron Ore	23.85	...	7.40	4.26	...	0.16	22.6	1.73	0.40	0.35	...	1.25	0.07	0.32	<i>22.1</i>	<i>25.8</i>
308	...	Grecian Chrome Ore	...	15.3	4.25	19.4	41.5	<i>0.16</i>	0.34	16.4	<i>0.14</i>	<i>0.04</i>	<i>0.01</i>	<i>0.9</i>

Fluorspar & Bauxite (Finely divided material - units of 100g)

BCS-CRM No.	Description	Fe ₂ O ₃	SiO ₂	Al ₂ O ₃	CaF ₂	TiO ₂	CaO	MgO	BaO	Na ₂ O	K ₂ O	S	CO ₂	Cr	Cu	Mn	Ni	Pb	Sr	Zn	L.O.I.
392	Fluorspar	...	0.67	...	97.2	...	0.52	...	0.37	0.12	0.48	0.18
395	Bauxite	16.3	1.24	52.4	...	1.93	0.05	0.02	...	<i>0.02</i>	<i>0.02</i>	<i>0.0453</i>	<i>0.0021</i>	<i>0.0042</i>	<i>0.0034</i>	<i>0.0028</i>	<i>0.0023</i>	<i>0.0043</i>	27.8

Tin Ore (Finely divided material - units of 100g)

BCS-CRM No.	Description	Sn	Fe	Cu	As	Bi	Zn	Pb	S	W	Ni	Si	Ti	Al	Ca	F
355	Tin Ore	31.42	17.08	0.085	0.14	0.015	0.059	0.012	0.50	0.35	0.0040	7.14	0.37	4.12	2.63	2.07

Ores & Dust (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	F	V	Cr	Ni	C	Zn	Pb	Cl _(sol)	Co	Cu	Hg	LOI
517	...	Brazilian Iron Ore	66.30	0.519	0.033	0.0311	0.508	0.0332	0.679	0.0408	0.0090	0.0097	0.0105	...	0.0040	0.061	0.0047	0.0028	0.00075	...	0.0088	...	1.898
...	676-1	Iron Ore Sinter	39.76	6.40	12.78	1.16	3.40	0.19	0.83	0.59	0.12	0.095	0.43	0.10	0.070
...	681-1	Iron Ore	33.21	8.32	2.80	0.89	5.62	0.29	0.22	0.88	0.103	0.068	0.49	0.19	0.077	0.041	0.016	1.80	...	<i>0.0072</i>	...	<i>0.008</i>	
...	682-2	Iron Ore	66.12	0.833	<i>0.007</i>	0.0133	0.325	0.0441	0.0311	0.0529	0.0140	<i>0.003</i>	0.0015	<i>0.0015</i>	<i>0.0014</i>	0.0004	...	<i>0.0006</i>	0.0005	<i><1µg/g (3.01)</i>	
...	683-1	Iron Ore Sinter	56.06	3.38	5.70	1.04	1.30	0.097	0.462	0.148	<i>0.013</i>	0.045	0.148	0.020	0.026	0.018	0.010	

Slags (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	SiO ₂	TiO ₂	Al ₂ O ₃	Fe	FeO	CaO	MgO	Cr ₂ O ₃	MnO	V ₂ O ₅	P ₂ O ₅ (Cit Sol)	P ₂ O ₅ (Form Sol)	P ₂ O ₅ (Total)	S	F
381	...	Basic Slag	8.78	0.35	0.67	13.3	3.69	49.0	1.03	0.33	3.16	0.94	15.2	...	15.7	0.19	...
...	879-1	Basic Slag	8.82	0.535	0.803	18.97	...	43.70	2.19	0.477	4.45	0.738	7.59	<i>5.73</i>	8.46	0.102	0.368

Tungsten Carbides (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C (Total)	C (Free)	Fe	O
352/1	...	Tungsten Carbide	6.154	0.036	0.0029	<i>0.11</i>
...	783-1	Tungsten Carbide	6.188	<i>0.04</i>	0.0022	<i>0.01</i>

Silicon Carbide Refractories (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C (Total)	Si (Total)	Al (Total)	C (Free)	Si (Free)	Fe (Total)	Mn	P	Cr	Mo	Ni	B	O	N	Ti	V	Ca	Mg	Na	K
...	781-1	Silicon Carbide Refractory	48.25	35.56	4.39	<i>37.22</i>	<i>4.646</i>	<i>0.8061</i>	<i>0.0274</i>	<i>0.0117</i>	<i>0.0240</i>	<i>0.0264</i>	<i>0.0210</i>	<i>0.0149</i>	...	<i>0.0282</i>	<i>0.0320</i>	<i>0.0216</i>	<i>0.0433</i>	<i>0.0421</i>	<i>0.0308</i>	<i>0.3765</i>
359	...	Nitrogen Bearing Silicon Carbide	23.46	67.6	0.118	<i>0.061</i>	<i>0.325</i>	0.175	<i><0.01</i>	<i>0.014</i>	...	<i>0.532</i>	<i>7.84</i>	0.022	<i>0.027</i>	0.108	<i><0.01</i>	<i><0.01</i>	<i><0.01</i>
360	...	Sialon Bonded Silicon Carbide	23.53	60.8	6.52	<i>0.085</i>	<i>0.538</i>	<i>0.19</i>	<i><0.01</i>	...	<i><0.01</i>	...	<i>0.013</i>	...	<i>4.03</i>	<i>4.77</i>	0.025	...	0.115	<i><0.02</i>	<i><0.01</i>	<i><0.01</i>

BRITISH CHEMICAL STANDARD CERTIFIED REFERENCE MATERIALS - Ceramic Materials and Minerals

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Ceramic Materials & Minerals (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	MnO	Mn ₂ O ₄	CaO	MgO	Na ₂ O	K ₂ O	PbO	ZnO	P ₂ O ₅	ZrO ₂	S	L.O.I.
309	...	Sillimanite	34.1	61.1	1.92	1.51	0.03	...	0.22	0.17	0.34	0.46	0.1
313/1	...	High Purity Silica	99.78	0.036	0.017	0.012	0.00013	...	0.006	0.0013	0.003	0.005	0.002	...	0.1
319/1	...	Magnesia	1.093	0.109	0.0070	0.291	0.108	...	3.00	95.38	0.007	0.0008
348	...	Ball Clay	51.1	31.6	1.08	1.04	0.17	0.30	0.34	2.23	0.071	0.03	0.1	11.8
358	...	Zirconia	0.20	0.08	0.20	0.064	1.50	3.42	<0.01	<0.01	92.70	...	0.08
362 [#]	...	Mine Tailings Sample	9.03	0.667	0.047	0.483	...	0.829	44.21	0.068	0.084	0.14	2.63	2.59	0.014	...	1.48	32.81
369	...	Magnesite-Chrome	2.59	14.7	0.14	10.3	0.11	...	1.17	53.5	0.05	0.03
370	...	Magnesite-Chrome	3.01	12.3	0.13	7.23	0.11	...	1.54	61.8	0.06	0.03
375/1*	...	Soda Feldspar	69.26	17.89	0.313	0.291	...	Mn ₂ O ₃	0.78	0.180	8.89	1.47	0.0004	0.0005	0.226	0.0107	...	0.72
376/1	...	Potash Feldspar	65.77	18.63	<0.01	0.085	...	0.004	0.421	0.03	3.00	11.59	0.0090	...	0.02	<0.01	...	0.203
388	...	Zircon	32.7	0.291	0.232	0.049	0.04	<0.05	<0.02	<0.03	0.12	64.9	...	0.20
389/1	...	High Purity Magnesia	0.274	0.104	0.0051	0.607	0.100	...	0.880	97.89	0.0029	0.0295	0.0008
393	752-1	Limestone	0.70	0.12	0.009	0.045	0.010	...	55.4	0.15	0.02	0.02	0.005	...	0.007	43.4
396	...	Low Silica Magnesite Chrome	1.37	5.73	0.26	10.9	0.17	...	1.12	64.6	0.06	0.03	0.04
512	...	Dolomite	0.379	0.055	0.0020	0.030	0.0036	...	30.61	21.59	0.1	<0.02	<0.001	<0.01	<0.02	...	<0.05	46.80
513	...	Limestone	0.228	0.108	0.004	0.0275	0.0095	...	55.59	0.182	<0.3	0.0150	0.0009 Pb	0.0014 Zn	0.005	...	0.0097	43.61
516	...	Standard Glass Sand	98.73	0.513	0.172	0.0596	...	0.0012	0.0243	0.0387	0.0195	0.127	0.0127	<0.01	0.013	0.075	...	0.24
...	776-1	Firebrick	62.76	29.28	1.62	1.43	0.310	0.476	0.488	2.92	0.062	0.04	...	0.3
...	782-1	Dolomite	0.266	0.104	0.0042	0.450	0.081	...	30.34	21.29	...	0.0260	0.0029	0.0082	0.0128	...	0.016	47.25

[#] Additional certified values available for Aqua Regia soluble content and pH in BCS-CRM 362: As=0.0030%, Cd=0.0200%, Cr=0.0011%, Cu=0.0056%, Ni=0.0012%, Pb=2.30%, Zn=2.03% and pH=8.14

*Information is also given on approximate levels of Ce, Cs, Eu, Ga, La, Nb, Nd, Rb, Sc, Sm and Yb in BCS-CRM 375/1

Ceramic Materials & Minerals (continued)

BCS-CRM No	ECRM No	Description	B ₂ O ₃	BaO	Cr ₂ O ₃	HfO ₂	Li ₂ O	SrO	ThO ₂	U ₃ O ₈	Y ₂ O ₃	As	C	Cd	F	Ni
309	...	Sillimanite	...	0.006	0.01	0.003
313/1	...	High Purity Silica	<0.0002	...	0.0005
319/1	...	Magnesia	0.002	0.0038	0.0035	0.0060	0.0014	0.0075
348	...	Ball Clay	...	0.04	0.016	1.64
358	...	Zirconia	...	0.10	...	1.63	...	0.07	0.0007	0.08
362 [#]	...	Mine Tailings Sample	...	2.02	0.003	0.034	9.9	0.020	...	0.001
369	...	Magnesite-Chrome	...	<0.01	17.2	...	0.03	<0.01	0.15
370	...	Magnesite-Chrome	...	<0.01	13.4	...	0.03	<0.01	0.08
375/1*	...	Soda Feldspar	...	0.0106	0.0018	0.0004	...	0.012	0.0011	0.0002	0.0023
376/1	...	Potash Feldspar	...	0.0210	0.001
388	...	Zircon	1.30	0.018	0.034	0.136
389/1	...	High Purity Magnesia	0.015	0.0015	0.004	0.0007	0.0029	0.0012
393	752-1	Limestone	...	0.006	0.019	<0.01	...
396	...	Low Silica Magnesite Chrome	0.09	...	15.6	...	0.05
512	...	Dolomite	...	<0.02	<0.001	0.024	<0.003	12.4	<0.0003	0.01	<0.001
513	...	Limestone	...	0.01	0.0012	0.0176	<0.001	11.9	<0.001	0.002	<0.001
516	...	Standard Glass Sand	...	0.0040	0.0081	<0.01	...	<0.01
...	776-1	Firebrick	...	0.122	0.022	...	0.019
...	782-1	Dolomite	0.0039	0.0008	0.0009	0.0004

BRITISH CHEMICAL STANDARD - REFERENCE MATERIALS - High Purity Metals, Ceramic Materials and Benzoic Acids

Although these samples have been carefully analysed by both BAS Ltd. and an independent laboratory, they have been classified as RMs and not CRMs in order to distinguish them from BAS CRMs which are normally analysed by at least five laboratories.

CHEMICAL COMPOSITION (nominal mass content in %)

High Purity Metals (Finely divided material or blocks/bars - see below)

BCS-RM No.	Description	Cu	Sn	Zn	Pb	Ni	Fe	Al	Mn	Sb	Si
192g	High Purity Tin (300g blocks)	0.00007	99.997	0.00006	0.0007	<0.00005	0.0002	0.0007	...
192h	High Purity Tin (100g millings)	<0.0001	99.998	<0.0001	0.0006	<0.0001	<0.0001	<0.0005	...
194e	High Purity Zinc (300g blocks)	<0.0005	<0.001	99.99	0.002	...	0.001
195g	High Purity Aluminium (100g millings or 300g blocks)	0.001	...	0.015	0.080	99.85	0.001	...	0.035
198f	Super Pure Aluminium (100g blocks)	0.005	0.001	99.99	0.002
210e	High Purity Lead (500g bars)	0.0006	<0.002	<0.005	99.996	<0.001	0.0005	<0.001	<0.001	<0.002	...

High Purity Metals (continued)

BCS-RM No.	Description	Bi	Ti	Ag	C	S	V	Tl	Ga	Melting Point
192g	High Purity Tin (continued)	0.00003	0.001	0.0002	231.9°C
192h	High Purity Tin (continued)	<0.0001	0.001	0.0002	231.9°C
194e	High Purity Zinc (continued)	419.5°C
195g	High Purity Aluminium (continued)	...	0.002	0.004	...	0.009	659.2°C
210e	High Purity Lead (continued)	0.0008	...	0.0001	0.001	...	327.3°C

Ceramic Materials (Finely divided material - units of 100g). These samples have been prepared jointly by Ceram Research Limited and BAS.

BCS-RM No.	Description	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	P ₂ O ₅	BaO	Mn ₂ O ₃	SnO ₂	SrO	SO ₃	ZrO ₂ + HfO ₂	L.O.I.
201a	Nepheline Syenite	57.3	23.54	0.05	0.12	1.07	0.025	7.53	8.90	0.025	0.37	0.007	...	0.43	0.76
202a	Plaster (Gypsum)	1.38	0.33	0.03	0.10	37.4	0.39	<0.03	0.10	<0.01	0.33	53	...	7.0
203a	Talc	59.7	0.30	<0.01	0.22	0.25	32.08	0.02	0.005	0.13	6.78
204a	Zircon	37.6	0.74	2.22	0.18	0.15	0.012	0.014	0.017	0.77	1.69	53.8	0.50

Benzoic Acid (Finely divided material - units of 100g; also available as 0.2g and as 1.0g tablets)

BCS-RM No.	Description	
190t	Benzoic Acid	Purity 100.0±0.05%, Calorific Value, 26,439.7±12.2 joules per gramme based on mass (Certified by Pattinson and Stead, Middlesbrough, UK)

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - Unalloyed Steels

The figures are listed primarily as a guide to purchasers. In some cases provisional figures are given which may differ slightly from those given on the Certificate. **Always consult the Certificate issued with the sample to obtain the accurate analysis.**

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Plain Carbon Steels (Wrought) (SS-CRM: 38mm dia. x 19mm discs, ECRM: 38mm dia. x 30 or 25mm discs except 056-2(D): 44mm dia. x 30 or 25mm discs)

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol)	Al (Total)	As	Co	Cu	N	Nb	Pb	Sn	Ti	V	Ca	Sb	Zn	
SS-CRM 432/1	Plain Carbon Steels	0.102	0.043	1.34	0.024	0.039	0.31	0.02	0.14	...	0.01	0.04	...	<0.002	
SS-CRM 433/1		0.195	0.18	0.60	0.074	0.069	0.26	0.01	0.064	...	<0.01	0.06	...	0.020	
SS-CRM 434/1		0.41	0.31	1.49	0.050	0.027	0.055	0.01	0.044	...	<0.01	0.05	...	0.078
SS-CRM 435/1		0.52	0.54	0.41	0.033	0.031	0.14	<0.01	0.060	...	<0.01	0.05	...	0.039
SS-CRM 431/2	Plain Carbon Steels	0.0249	0.015	0.902	0.121	0.0065	0.049	0.004	0.040	0.006	...	0.0052	0.0040
SS-CRM 432/2		0.0065	0.0822	0.712	0.0171	0.036	0.0166	0.002	0.0196	0.006	...	0.0066	0.0174
SS-CRM 433/2		0.096	0.0071	1.188	0.011	0.0083	0.0262	0.004	0.037	0.006	0.0590
SS-CRM 434/2		0.275	0.510	1.546	0.0611	0.0141	0.238	0.014	0.037	0.006	...	0.0104	0.038
SS-CRM 435/2	0.489	0.328	0.390	0.0373	0.0424	0.184	0.018	0.133	0.0116	0.134	
ECRM 056-2(D)	0.8% Carbon Steel	0.8181	0.2006	0.5073	0.0103	0.0093	0.0146	...	0.0218	0.00024	<0.001	0.0129
ECRM 057-2(D)	0.05% Carbon Steel	0.0507	0.003	0.246	0.0120	0.0127	0.0114	...	0.0096	...	0.059	0.0146	0.0023
ECRM 058-2(D)	0.15% Sulphur Steel	0.424	0.1080	1.186*	0.0098	0.1712*	0.1211	0.0589	0.199	0.0095	...	0.261	0.0107
ECRM 059-2(D)	0.7% Carbon Steel	0.721	0.188	0.495	0.0046	0.0084	0.0090	0.0018	0.0198	0.00020	0.00045	0.0074	0.0051
ECRM 064-1(D)	Nb/Ti Interstitial Free Steel	0.0026	0.0065	0.1641	0.0091	0.0104	0.0184	0.00077	0.0115	0.0302	0.0330	0.0036	0.0027	0.0077	0.0026	0.0146	0.00018	0.00051	0.0189	0.00015
ECRM 084-1(D)	0.4% Carbon Steel	0.391	0.265	0.860	0.018	0.029	...	0.033	0.154	0.267	0.023
ECRM 085-1(D)	0.3% Sulphur Steel	0.067	0.008	0.977*	0.062	0.336*	0.019	0.291	...	0.0010	0.0021	...	0.0073	0.002	...	
ECRM 086-1(D)	0.3% Carbon Steel	0.297	0.206	0.879	0.0238	0.0371	0.150	...	0.168	0.0230	...	0.320	0.0263
ECRM 087-1(D)	0.15% Carbon Steel	0.174	0.263	0.671	0.010	0.046	0.078	0.021	0.118	0.024	0.015	0.171	0.017	0.0046	...	
ECRM 090-1(D)	1% Carbon Steel	1.054	0.281	0.226	0.0128	0.0095	0.121	0.0089	0.053	0.0146	0.00043	0.204
ECRM 096-2(D)	Low S, Ca-Treated Steel	0.1050	0.262	1.320	0.0128	0.0016	0.0243	0.0020	0.0253	...	0.0460	...	0.0170	0.0252	0.0020

*The metallurgical conditions of ECRMs 058-2(D) and 085-1(D) render them unsuitable for the determination of Mn and S by Optical Emission Spectrometry.

Plain Carbon Steels (Wrought) (continued)

Ref No.	Description	Bi	Cd	Ga	Hg	Pb	Sb	Se	Te	Tl	Zn
ECRM 090-1(D)	1% Carbon Steel	<0.00002	<0.00002	0.00228	<0.00001	0.00239	0.00090	<0.0002	<0.0002	<0.0001	0.00209

Carbon Steels Residual Series (Wrought) (38mm dia. x 19mm discs except SS-CRM 51: 38mm dia. x 13mm discs)

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	Cu	Pb	Sn	Ti	W	Sb
SS-CRM 51	Carbon Steel Residual Series	0.38	0.12	0.13	0.018	0.010	0.106	0.068	0.099	0.12	0.003	0.014	0.13 ₀	0.077	0.003
SS-CRM 53		0.25	0.37	0.29	0.02	0.009	0.22	0.100	0.172	...	0.058	0.024	0.018	0.25	0.004
SS-CRM 55		0.19	0.25	0.42	0.018	0.010	0.22	0.16	0.23	0.028	0.013	0.046	0.013	0.12	0.002
SS-CRM 453/1		0.160	0.34	1.38	0.044	0.026	0.26	0.081	0.11	...	0.052	0.099	0.0001	0.022	0.073	0.30	...
SS-CRM 454/1		0.376	0.31	0.80	0.061	0.047	0.062	0.20	0.069	...	0.070	0.051	0.0001	0.054	0.010	0.15	...
Ref No.	Description	C	Si	Mn	P	S	Al (Acid Sol)	Al (Total)	B	Co	Cu	Nb	Pb	V	Zr	Sb	
SS-CRM 56	Carbon Steel Residual Series	0.23	0.36	0.32	0.019	0.009	0.003	0.005	0.001	0.023	0.36	...	0.014	0.057	...	0.005	
SS-CRM 458/1		0.247	0.54	0.49	0.032	0.033	...	0.023	...	0.21	...	0.052	0.0078	0.108	0.050	0.072	
SS-CRM 456/2		0.112	0.297	0.220	0.0212	0.0221	<0.002	0.0018	0.0015	0.0504	...	0.0057	0.0189	0.0221	0.013	0.0172	
SS-CRM 457/2		0.307	0.105	0.327	0.0098	0.0448	0.082	0.087	0.0046	0.0217	...	0.0174	0.0098	0.153	0.025	0.050	
SS-CRM 458/2		0.198	0.504	0.479	0.0281	0.0314	0.052	0.055	0.0069	0.198	...	0.0510	0.0140	0.105	0.062	0.089	
SS-CRM 459/2		0.467	0.640	0.909	0.0482	0.0481	0.0134	0.0154	0.0110	0.0890	...	0.0102	0.0044	0.0585	0.074	0.0121	
SS-CRM 460/2		0.383	0.126	0.616	0.0374	0.0099	0.0193	0.0240	0.0027	0.0106	...	0.068	0.0005	0.0322	<0.0005	0.0006	

Many of the above samples are also available in the finely divided form - see pages 7 and 8.

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - High Purity Iron and Low Alloy Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

High Purity Iron (Wrought) (38mm dia. x 30, 25mm or 3mm discs)

Ref No.	Description	C	Si	Mn	P	S	Cr	Ni	As	B	Co	Cu	N	Sn	Ti	O	Zn	W,Sb	Mo,Nb,V,Zr	Pb,Bi,Ca,Mg,Ta
ECRM 097-1(D)	High Purity Iron	0.00025	<0.01	0.0064	0.0016	0.0022	0.0016	0.0025	0.0051	0.0003	0.0037	0.0020	0.0007	<0.0025	<0.0015	0.05	<0.0001	≤0.001	<0.001	<0.0005

Low Alloy Steels (Wrought) (SS-CRM 111-114: 44mm dia. x 19 or 50mm discs. Other SS-CRM: 38mm dia. x 19mm discs. ECRM: 38mm dia. x 30 or 25mm discs)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	W	Zr	Ca	Sb	Zn
SS-CRM 111	Low Alloy Steels	0.0258	0.0253	0.155	0.0033	0.0054	0.0197	0.0008	0.0387	0.0348	0.0017	<0.001	0.0144	0.0171	0.0034	0.0005	<0.001	0.0015	0.0004	0.0009	...	<0.001	<0.0005	<0.001	...
SS-CRM 112		0.394	0.289	0.436	0.0043	0.0026	1.236	0.190	1.461	0.0148	0.0021	0.0007	0.0175	0.149	0.0024	0.0065	<0.001	0.0086	0.0100	0.0088	...	<0.001	<0.0005	<0.001	...
SS-CRM 113		0.837	0.931	1.207	0.0595	0.0294	1.248	0.056	0.0784	0.0151	0.0020	0.0066	0.0415	0.179	0.0109	0.0487	<0.001	0.0067	0.0390	0.201	0.012	0.0029	<0.001	<0.003	...
SS-CRM 114		0.403	0.295	0.416	0.0044	0.0046	0.187	0.184	1.502	0.078	0.0025	0.0008	0.0171	0.360	0.0043	0.0042	<0.001	0.041	0.0096	0.0086	<0.001	0.0051	<0.001	<0.0025	...
SS-CRM 401/2	Low Alloy Steels	0.935	0.602	1.197	0.0265	0.0078	0.138	0.495	0.019	0.074	0.0042	0.101	0.015	0.496
SS-CRM 402/2		1.311	0.111	0.228	0.0161	0.0138	0.652	0.140	0.808	0.161	0.302	0.0069	0.194
SS-CRM 403/2		0.750	0.209	1.677	0.055	0.0381	0.463	0.088	0.223	0.0485	0.221	0.010	0.341
SS-CRM 404/2		0.696	1.121	0.532	0.0479	0.0228	0.774	0.307	0.393	0.017	0.427	0.0089	0.107
SS-CRM 405/2		0.044	0.947	0.903	0.0095	0.058	0.206	0.025	0.102	0.330	0.009	0.022	0.011	0.411
SS-CRM 406/2		0.173	0.342	0.447	0.0102	0.043	2.001	0.98	1.62	0.013	0.012	...	0.006	0.289	0.009	...	0.0002	0.001	...	0.010
SS-CRM 407/2		0.490	0.66	0.195	0.038	0.0105	3.03	0.83	0.527	0.040	0.0068	0.397	0.011	0.19
SS-CRM 408/2		0.289	0.237	0.557	0.056	0.030	0.111	0.098	4.13	0.154	0.0046	0.694	0.0075	...	0.0006	0.002	...	0.067
SS-CRM 409/2		0.086	1.18	0.559	0.0141	0.0179	1.318	0.599	3.02	0.094	0.205	0.0108	0.008
SS-CRM 410/2		0.428	1.10	0.419	0.074	0.041	1.684	0.432	2.07	0.046	0.0053	...	0.0248	0.436	0.0155	0.44
SS-CRM 421	Low Tungsten Steels	0.049	0.07	0.11	0.012	0.027	...	0.028	<0.02	0.52
SS-CRM 422		0.036	0.06	0.09	0.015	0.025	...	0.033	<0.02	1.28
SS-CRM 423		0.030	0.05	0.07	0.017	0.027	...	0.027	<0.02	2.06
SS-CRM 424		0.024	0.05	0.09	0.02	0.024	...	0.036	<0.02	3.02
ECRM 186-1(D)	Si-Mn Steel	0.6104	1.719	0.870	0.0223	0.0354	0.218	0.0482	0.190	0.0143	0.281	
ECRM 195-1(D)	Cr-Mo-Ni Steel	0.73	0.466	0.571	0.0160	0.0121	1.566	0.768	0.327	0.0355	0.0100	...	0.0010	0.002	...	0.312	0.0017	0.0008	0.0046	

Most of these samples are also available in the finely divided form - see page 9.

Low Alloy Cast Steels (44mm dia. x 19mm discs)

Ref. No.	Description	C	Si	Mn	S	Cr	Mo	Ni	Cu	V
SS-CRM 612/1	Low Alloy Cast Steels	0.12	0.28	0.60	0.02	4.14	0.80	0.97	0.06	0.21
SS-CRM 614/1		0.41	0.39	1.30	0.02	1.18	0.60	3.05	0.06	0.27
SS-CRM 615/1		0.30	0.17	1.68	0.02	0.49	0.21	4.01	0.05	0.10

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - Highly Alloyed Steels and Plain Carbon Cast Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Highly Alloyed Steels (Wrought) (38mm dia. x 30 or 25mm discs)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	Zr	Sb	Fe	Others
ECRM 272-1(D)	12% Chromium Steel	0.2815	0.420	0.600	0.0156	0.0197	11.927	0.0030	0.244	0.0046	0.0116	0.0018	0.0145	0.0192	0.0508	0.0028	0.0004	0.0008	0.00096	0.0167	...	0.0007	...	0.00090 Ca 0.0031 Zn
ECRM 276-2(D)	5%Cr-Mo-V Steel	0.399	1.034	0.365	0.0093	0.0189	4.975	1.134	0.203	0.183	0.0116	0.0133	...	0.296
ECRM 285-2(D)	Maraging Steel	0.0018	0.0117	0.0168	0.0053	0.0025	0.0236	4.99	18.07	0.1067	...	0.0009	7.76	0.0094	0.0007	0.001	0.520	...	0.0050
ECRM 287-1(D)	High B Stainless Steel	0.0164	0.569	1.478	0.0267	0.0014	18.61	0.247	10.35	0.924	0.148	0.203	0.0194
ECRM 292-1(D)	Nb-Stabilised Stainless Steel	0.0367	0.402	1.744	0.0175	0.0055	18.00	0.0464	10.09	0.002	0.008	0.0003	0.0255	0.0391	0.0640	0.571	{ 0.001 Ta 0.0006 Ca
ECRM 295-1(D)	4% Mo-Cr-Ni Steel	0.0166	0.418	1.758	0.0167	0.0003	19.51	3.996	24.40	0.0203	0.0041	0.0018	0.0450	1.481	0.0615	0.0025	...	0.0456	...	0.0007	48.36	0.0003 Mg
ECRM 296-1(D)	Jethete Steel	0.1166	0.242	0.676	0.0178	0.0026	11.82	1.700	2.790	0.0275	0.0139	0.0003	0.0218	0.1498	0.0214	...	0.00016	0.0131	...	0.363

These samples are also available in the finely divided form - see page 10

Austenitic Stainless Steels (Wrought) (38mm dia. x 19mm discs)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	Ta	
SS-CRM 462	Austenitic Stainless Steels	0.092	0.46	0.74	0.010	0.018	12.35	...	12.55	...	0.007	0.0005	
SS-CRM 461/1		0.0103	0.374	0.686	0.0053	0.0051	14.727	0.0138	6.124	0.002	0.004	...	0.004	0.0091	0.0005	
SS-CRM 462/1		0.0345	0.463	0.722	0.0053	0.0041	11.888	0.0304	12.85	0.0112	
SS-CRM 463/1		0.019	0.270	1.400	0.025	0.019	18.46	0.265	10.20	0.0022	0.116	0.276	0.063	<0.005	0.04	...
SS-CRM 464/1		0.086	0.57	0.791	0.020	0.028	25.39	...	20.05	...	0.003	...	0.054	0.0004	
SS-CRM 465/1		0.066	0.405	1.380	0.021	0.012	17.31	0.092	9.24	0.026	...	0.0006	0.053	0.098	0.010	...	<0.001	...	0.40	0.102	...	
SS-CRM 466/2		0.0141	0.480	1.311	0.0105	0.0069	17.84	2.776	10.20	0.002	0.0020	0.0039	0.0184	0.0278	0.0508	0.001	<0.0001	<0.001	0.002	0.0346	...	
SS-CRM 467/1		0.082	0.52	0.788	0.018	0.019	18.09	...	9.21	...	0.004	0.99	0.004	0.0017	
SS-CRM 468/1		0.143	1.41	1.70	0.014	0.020	17.96	...	8.90	0.018	
SS-CRM 475		0.050	0.21	0.89	0.037	0.008	14.14	1.59	5.66	0.013	0.22	1.94	...	0.22	...	0.015	

These samples are also available in the finely divided form - see page 10

Plain Carbon Cast Steels (44mm dia. x 19mm discs)

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	Co	Cu	V	Zr
SS-CRM 601/2	Plain Carbon Cast Steels	0.102	0.263	1.30	0.034	0.024	0.14	0.006	0.03	0.033	0.09	0.04	0.002	<0.005
SS-CRM 602/2		0.94	0.057	0.66	0.023	0.031	0.03	0.004	0.02	0.096	0.007	0.06	0.001	<0.005
SS-CRM 603/2		0.78	0.97	0.236	0.020	0.056	0.04	0.004	0.03	0.076	0.01	0.05	0.001	<0.005
SS-CRM 604/2		0.199	0.75	1.91	0.016	0.072	0.06	0.02	0.09	0.008	0.01	0.07	0.001	<0.005
SS-CRM 605/2		0.400	0.54	0.345	0.054	0.015	0.06	0.01	0.05	0.027	0.008	0.06	0.001	0.12

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - Highly Alloyed Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Ferritic Stainless Steels (Wrought) (SS-CRM 469-473: 38mm dia. x 19mm discs, SS-CRM 70: 44mm dia. x 13mm disc)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Co	Cu	V
SS-CRM 70	Ferritic Stainless Steels	0.18	0.35	0.38	0.024	0.020	16.35	...	0.40	...	<i>0.06</i>	...
SS-CRM 469		0.279	0.421	0.598	0.015	0.020	11.93	...	0.246	<i>0.01</i>	<i>0.02</i>	<i>0.02</i>
SS-CRM 470		0.153	0.335	0.235	0.024	0.035	17.68	...	0.369	<i>0.02</i>	<i>0.02</i>	<i>0.02</i>
SS-CRM 471		0.095	0.326	0.417	0.018	0.023	23.85	...	0.96	<i>0.02</i>	<i>0.02</i>	<i>0.03</i>
SS-CRM 472		0.227	1.05	1.02	0.032	0.029	15.82	0.661	1.95	<i>0.02</i>	<i>0.02</i>	<i>0.02</i>
SS-CRM 473		0.172	0.604	0.494	0.019	0.030	9.06	0.95	<i>0.06</i>	<i>0.01</i>	<i>0.03</i>	<i>0.02</i>

Samples 469 to 473 are also available in the finely divided form - see page 10

High Speed Tool Steels (Wrought) (38mm dia. x 19mm discs)

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Co	Sn	V	W
SS-CRM 481/1	High Speed Tool Steels	0.68	0.15	0.25	0.023	0.022	3.40	0.28	<i>0.09</i>	0.31	...	0.56	14.0
SS-CRM 482/1		0.67	0.14	0.26	0.027	0.027	3.95	0.40	<i>0.16</i>	0.29	...	1.04	17.8
SS-CRM 483/1		0.65	0.16	0.22	0.023	0.023	2.90	0.18	<i>0.08</i>	2.06	...	0.22	9.28
SS-CRM 485/1		0.94	0.30	0.41	0.043	0.039	4.02	0.66	<i>0.14</i>	<i>0.006</i>	<i>0.022</i>	4.97	0.019	1.02	17.8
SS-CRM 486/1		0.74	0.27	0.21	0.029	0.021	4.54	5.20	<i>0.06</i>	<i>0.005</i>	<i>0.016</i>	0.08	0.014	1.82	5.80
SS-CRM 487/1		1.02	0.18	0.26	0.022	0.029	3.91	9.41	<i>0.14</i>	0.006	<i>0.012</i>	7.95	<i>0.006</i>	1.14	1.80

High Manganese Steels (Cast) (48mm x 42mm x 12mm blocks, except 491/2: 50mm dia. x 10mm chill cast disc). These samples have been prepared jointly by Castings Technology International (formerly BCIRA) and BAS.

Ref Nos.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	N	V	As	Sn	Ti
SS-CRM 491/2	High Manganese Steels	0.994	1.101	16.73	0.0494	0.0112	1.482	0.608	0.0745	0.110	...	<i>0.04</i>	0.0215	0.0839
SS-CRM 492/3		1.18	0.299	8.33	0.0318	0.0093	1.076	1.318	4.17	0.131	0.0048	0.0211	0.0225	<i>0.004</i>	<i>0.002</i>	...	0.0024
SS-CRM 495/4		0.796	0.674	13.11	0.093	0.0128	2.223	0.266	1.620	0.0082	0.0120	0.0222	0.0416	0.0525	<i>0.02</i>	<i><0.05</i>	<i><0.002</i>

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - Cast Irons and Nickel Base Alloys

CHEMICAL COMPOSITION - Figures in bold type certified, figures in small italic type only approximate.

Cast Irons (All are 48mm x 42mm x 12mm chill cast blocks except SCRM 671-675 which are 40mm x 37mm x 10mm chill cast blocks.)

These samples are prepared jointly by Castings Technology International (formerly BCIRA) and BAS. nominal mass content in %

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Co	Cu	Sn	Ti	V	Ce	Mg	Zn
SCRM 651/4	Malleable Irons	2.66	0.541	0.92	0.249	0.100	<i>1</i>
SCRM 652/4		2.34	0.878	1.19	0.071	0.129	<i>1</i>
SCRM 653/4		3.10	1.22	0.110	0.023	0.050	<i>1</i>
SCRM 654/4		2.28	1.635	0.74	0.130	0.170	<i>1</i>
SCRM 655/4		1.90	2.110	0.44	0.180	0.076	<i>1</i>
SCRM 656/8	Low Phosphorus Engineering Irons	2.61	2.59	0.823	0.062	0.107	<i>1</i>
SCRM 657/8		2.93	3.02	0.062	0.100	0.024	<i>1</i>
SCRM 658/10		3.338	1.943	0.532	0.187	0.074
SCRM 659/8		3.96	1.40	1.00	0.025	0.039	<i>1</i>
SCRM 660/9		3.461	1.699	0.406	0.153	0.105	<i>1</i>
SCRM 661/4	High Phosphorus Engineering Irons	2.56	2.96	0.30	0.84	0.068	<i>1</i>
SCRM 662/4		2.95	2.33	0.76	0.30	0.087	<i>1</i>
SCRM 663/4		3.28	1.97	1.04	0.13	0.024	<i>1</i>
SCRM 664/4		2.84	2.71	0.57	0.44	0.112	<i>1</i>
SCRM 665/4		3.25	1.66	0.24	1.09	0.053	<i>1</i>
SCRM 666/11	Ductile (Nodular) Irons	3.371	1.77	0.065	0.129	0.1070	1.648	0.0506	...	0.0860	0.0549	0.0035	0.073	...
SCRM 667/12		3.06	2.966	0.236	0.298	0.0063	1.298	0.550	...	0.0029	0.096	0.081	0.0400	...
SCRM 668/11		3.749	1.461	0.678	0.965	0.0233	0.127	0.754	...	0.0937	0.208	0.0232	0.0105	...
SCRM 669/12		3.009	2.634	0.563	0.203	0.061	0.445	0.235	...	0.0555	0.505	0.0415	0.0203	...
SCRM 670/14		3.541	2.320	0.358	0.513	0.0121	0.916	0.942	...	0.100	0.0249	0.0095	0.0384	...
SCRM 671	Blast Furnace Irons	2.865	0.980	0.835	0.1062	0.0499	0.0586	0.0182	0.0555	0.0379	0.0220	0.097	0.0470	0.0070	0.0896	0.0105	0.0004
SCRM 672		4.079	0.181	0.492	0.244	0.0379	0.0236	0.099	0.0826	0.0075	0.0039	0.156	0.0684	0.0018	0.0393	0.1093	0.0144
SCRM 673		2.474	1.715	0.1334	0.328	0.0067	0.0374	0.0057	0.143	0.0282	0.044	0.0540	0.0230	0.0191	0.0722	0.0586	0.0004
SCRM 674		3.322	0.474	1.457	0.0104	0.0810	0.0211	0.0477	0.144	0.0040	0.0275	0.0143	0.1014	0.0140	0.0233	0.0235	0.0187
SCRM 675		1.916	1.300	1.798	0.0453	0.0724	0.0794	0.0342	0.205	0.0072	0.0342	0.0230	0.0117	0.0062	0.0070	0.179	0.0006

Nickel Base Alloys (38, 41 or 50mm dia. x 13 or 19mm discs)

MAJOR ELEMENTS - nominal mass content in %

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	Nb	Ti	V	W	Zr	Fe	Sb
SS-CRM 310/1	Nimonic '90' Alloy	0.068	0.46	0.35	19.45	...	58.6	1.06	...	17.0	2.43	0.25	...
SS-CRM 345	IN 100 Alloy (cast)	0.153	9.95	3.01	Bal.	5.58	0.019	14.71	<i>5</i>	1.00	...	0.044
SS-CRM 346A	IN 100 Alloy (cast)	<i>0.15</i>	<i>10</i>	<i>3</i>	Bal.	<i>5.5</i>	...	<i>15</i>	<i>5</i>	<i>1</i>
SS-CRM 350	IN 713 Alloy (cast)	0.138	0.110	0.019	13.43	4.29	70.8	5.97	0.013	0.338	...	2.17	0.87	...	0.094	0.072	1.50	...
SS-CRM 351	IN 718 Alloy (wrought)	<i>0.025</i>	0.14	0.037	<i>0.006</i>	0.0006	18.12	3.06	53.1	0.55	0.0051	0.136	0.016	5.20	1.06	18.26	...
SS-CRM 363/1	Monel Alloy 400 (wrought)	0.140	0.028	1.26	...	<i>0.002</i>	<i>0.05</i>	...	64.7	0.027	...	0.032	31.90	...	<i>0.03</i>	1.86	...
SS-CRM 387/1	Nimonic 901 Alloy (wrought)	0.033	0.06	0.025	0.0033	0.0028	11.35	5.83	41.2	0.24	0.017	0.020	0.0076	...	3.00	38.4	0.0003

Nickel Base Alloys (continued)

TRACE ELEMENTS-nominal mass content in µg/g

Ref. No.	Description	Pb	Bi	Ag	Se	Te	Tl	Sb	As	Cd	Ga	Sn	Zn	Mg	Ca	In
SS-CRM 345	IN 100 Alloy	0.21	<0.2	<0.2	<0.5	<0.2	<0.2	<2	<i>2</i>	<0.1	8.2	5.6	<0.5	5.5	< <i>5</i>	...
SS-CRM 346A	IN 100 Alloy	22.2	10.3	42.5	5.7	9.3	1.9	45	50.4	0.37	49.6	93	28.8	130	<i>20</i>	<i>20</i>
SS-CRM 387/1	Nimonic 901 Alloy	<i>0.3</i>

SPECTROSCOPIC REFERENCE MATERIALS - Cast Irons

These samples are intended for the calibration of optical emission and XRF instruments with respect to the alloying and trace elements below. Although they have been carefully analysed by both BAS Ltd. and an independent laboratory, they have been classified as RMs and not CRMs in order to distinguish them from BAS CRMs which are normally analysed by at least five laboratories.

CHEMICAL COMPOSITION (nominal mass content in %)

Cast Iron Reference Materials (All are 40mm x 37mm x 10mm chill cast blocks except NIRM 2/1, NIRM 8/1, SIMO 1/2 and SIMO 2/2 which are 48mm x 42mm x 12mm chill cast blocks)

These samples have been prepared jointly by Castings Technology International (formerly BCIRA) and BAS

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu	Nb	Pb	Sn	Ti	V	Bi	Ce	Mg
LARM 1	Low Alloy Cast Irons	(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	0.50	...	0.49	0.006	...	2.49	0.14	0.11	0.011	0.005	...
LARM 2		(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	2.50	0.22	...	0.066	0.044	0.007	0.22	0.33	0.008	...
LARM 3		(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	1.80	0.042	0.092	0.003	...	1.20	0.55	0.022
LARM 4		(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	1.19	1.00	...	0.014	0.26	...	0.018	0.11	0.17	0.008	...
LARM 5		(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	...	0.62	2.46	...	0.018	0.0012	0.0005	0.025	...	0.24	0.0010
CRRM 1	High Chromium Cast Irons	1.91	1.56	1.43	0.114	0.072	11.35	3.08	2.07	1.97	...	0.008
CRRM 3		2.68	0.94	0.84	0.054	0.050	18.28	1.80	1.27	1.22	...	0.008
CRRM 1/1	High Chromium Cast Irons	1.83	1.53	1.45	0.132	0.099	11.18	3.05	2.03	0.117	2.01	0.096	0.040
CRRM 2/1		1.92	1.18	1.11	0.097	0.079	14.13	2.44	1.61	0.054	1.59	0.070	0.063
CRRM 3/1		2.42	0.82	0.85	0.068	0.059	17.48	1.65	1.28	0.084	1.21	0.021	0.022
CRRM 4/1		3.00	0.56	0.60	0.044	0.039	22.42	1.19	0.62	<0.005	0.58	0.027	0.092
CRRM 5/1		3.46	0.25	0.32	0.029	0.019	29.09	0.54	0.29	0.17	0.23	0.026	0.063
NCRM 1	Nickel Chromium Cast Irons	3.05	0.95	1.21	0.300	0.156	0.55	1.02	0.57	2.17
NCRM 2		2.97	1.82	0.95	0.068	0.119	1.99	0.36	2.10	1.67
NCRM 3		3.24	0.29	0.67	0.125	0.090	3.95	0.78	3.64	1.21
NCRM 4		2.66	2.13	0.40	0.203	0.012	7.94	0.57	5.34	0.68
NCRM 5		3.70	1.15	0.27	0.025	0.015	10.44	0.10	6.74	0.204
NIRM 1	Austenitic (Ni-Resist) Cast Irons	2.05	3.15	6.72	0.055	0.005	0.246	...	11.80	0.20	0.018	0.021
NIRM 2/1		2.81	1.50	2.08	0.129	0.010	1.48	...	13.95	5.98	0.015	0.050
NIRM 3		2.51	2.21	0.51	0.208	0.096	2.43	...	17.8	1.00	0.09	0.007	...
NIRM 4		1.97	3.03	2.37	0.051	0.008	3.56	...	20.2	0.52	0.37	0.011	0.014
NIRM 5		2.93	1.73	1.09	0.126	0.004	0.50	...	22.1	0.22	0.20	<0.002	0.040
NIRM 6		2.44	2.43	4.00	0.217	0.062	1.07	0.45	26.7	0.10	0.003	...
NIRM 7		2.05	3.05	0.71	0.058	0.020	3.53	0.99	32.9	0.52	0.005	0.019
NIRM 8/1		1.34	5.42	1.60	0.109	0.010	2.34	0.75	35.2	0.23	0.013	0.043
SIMO 1/2	Silicon Molybdenum Cast Irons	2.62	4.01	0.294	0.030	0.008	0.863	0.799	0.033	0.034	0.047	...	0.0022	0.025	0.049	0.006	0.005	0.038
SIMO 2/2		2.14	4.75	0.434	0.025	0.007	0.856	0.484	0.0189	0.013	0.039	...	0.0029	0.010	0.038	0.005	0.009	...	0.006	0.026

SPECTROSCOPIC STANDARD REFERENCE MATERIALS - Copper Base Alloys

These samples are intended for the calibration of optical emission and XRF instruments with respect to the alloying and trace elements below. Although they have been carefully analysed by both BAS Ltd. and an independent laboratory, they have been classified as RMs and not CRMs in order to distinguish them from BAS CRMs which are normally analysed by at least five laboratories.

Note that all CURM samples are now available in the finely divided (chip) form as well as in disc form

CHEMICAL COMPOSITION (nominal mass content in %)

Copper Base Alloy Reference Materials (Approx. 50mm dia. x 12 or 10mm discs)

Ref. No.	Description	Cu	Sn	Pb	Zn	Ni	P	Fe	Si	Mn	As	Sb	Bi	Al	S	Mg	Cr	Cd	Co	Ag	Te
CURM 09.01-4	Phosphorus Deoxidised Coppers	99.82	<0.001	<0.0005	0.0008	<0.0005	0.151	0.0019	<0.001	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.0005	0.011	<0.001
CURM 09.02-4		99.90	<0.001	<0.001	<0.001	<0.0005	0.078	0.0042	<0.002	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.0005	0.0055	<0.001
CURM 09.03-4		99.92	<0.001	<0.0005	<0.001	<0.0005	0.056	0.0033	<0.001	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.0005	0.012	<0.001
CURM 09.04-4		99.96	<0.001	<0.001	<0.001	<0.0005	0.0174	0.0047	<0.002	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	<0.0005	0.0033	<0.001
CURM 30.04-4	Main Elements in Brasses	64.34	0.009	0.003	35.62	<0.001	...	0.009	0.016	<0.001	<0.001	<0.005	<0.003	<0.001
CURM 30.05-4		69.48	<0.001	0.002	30.53	<0.0005	...	<0.003	0.001	<0.0005	<0.001	<0.005	<0.003	<0.001
CURM 30.09-4		89.53	<0.001	<0.001	10.45	<0.0003	...	0.0005	<0.001	<0.0003	<0.001	<0.001	<0.001	<0.001
CURM 30.11-4		59.86	<0.002	0.005	38.17	1.70	...	0.002	<0.001	0.23	<0.001	<0.001	<0.002	<0.001
CURM 30.15-4		60.66	<0.002	<0.005	38.88	<0.001	...	0.50	<0.005	<0.001	<0.005	<0.001	<0.001	<0.001
CURM 30.16-4		60.53	<0.002	<0.005	38.33	<0.001	...	1.14	<0.005	<0.001	<0.005	<0.001	<0.001	<0.001
CURM 30.18-4		63.66	0.58	<0.005	32.33	<0.001	...	0.006	0.131	<0.001	<0.005	<0.001	<0.001	3.28
CURM 30.20-4		61.46	0.40	<0.002	35.71	<0.001	...	<0.005	0.17	<0.001	<0.001	<0.002	<0.002	2.32
CURM 30.21-4	56.23	2.01	0.004	40.08	<0.001	...	0.003	0.213	<0.001	<0.001	<0.002	...	1.44	
CURM 42.21-2	Admiralty & Naval Brasses	66.78	0.60	0.259	31.61	0.120	0.087	0.119	0.15	<0.001	<0.003	0.25	0.013	0.003	0.034
CURM 42.22-2		70.46	1.10	1.10	26.32	0.061	0.177	0.23	0.042	0.122	0.217	0.173	0.046	0.042	<0.001
CURM 42.23-2		74.36	1.63	0.575	22.13	0.168	0.128	0.354	0.015	0.019	0.168	0.356	0.034	0.008	0.045
CURM 42.24-2		62.45	2.25	0.91	33.75	0.025	0.226	0.066	0.093	0.065	0.065	0.060	0.054	0.067	0.012
CURM 42.25-2		57.78	2.72	0.0023	39.20	<0.001	0.050	0.003	<0.001	0.169	0.118	<0.001	<0.001	0.021	0.005
CURM 43.01-4	Aluminium Brasses	74.36	0.116	<0.002	22.44	0.121	...	0.008	0.063	0.064	0.118	<0.001	<0.002	2.75
CURM 43.02-4		76.21	0.060	0.064	20.82	0.068	...	0.128	0.038	0.035	0.083	<0.001	<0.001	2.40
CURM 48.01-1	Cartridge Brasses	66.98	<0.002	0.106	32.6	0.134	0.016	0.049	0.041	<0.001	0.067	0.047	0.038	<0.001	<0.001	0.0008	<0.0005	<0.0003
CURM 48.02-1		67.16	0.035	0.084	32.58	<0.001	0.012	0.053	0.010	0.067	0.025	0.037	0.004	0.013	0.007	<0.0005	0.004	<0.0005
CURM 48.04-1		72.68	0.018	0.043	26.99	0.096	0.006	0.008	0.004	0.012	0.034	0.026	0.014	<0.001	0.011	0.0005	<0.002	<0.0003
CURM 48.05-1		68.69	0.083	<0.003	31.0	0.117	0.007	0.066	0.026	0.016	<0.001	<0.0005	<0.0005	<0.002	0.013	<0.0005	<0.0005	<0.0003
CURM 50.01-4	Leaded Bronzes	74.08	9.45	11.74	1.17	2.24	0.113	0.243	0.007	0.024	0.22	0.59	0.029	0.018	0.113
CURM 50.02-4		78.84	10.34	10.67	0.006	<0.0005	0.046	<0.001	<0.002	<0.0005	<0.002	<0.0005	<0.0005	<0.001	<0.001
CURM 50.03-4		77.42	8.41	8.86	1.72	2.89	0.159	0.018	0.005	0.037	0.11	0.24	0.051	0.005	0.064
CURM 50.04-4		76.11	11.30	9.94	0.66	1.10	0.032	0.10	0.011	0.028	0.06	0.50	0.10	0.014	0.14
CURM 51.11-4	Aluminium Bronzes	93.95	0.027	0.33	0.111	0.012	0.035	0.060	0.159	<0.001	<0.001	5.27
CURM 51.12-4		88.29	0.196	0.219	0.45	0.112	<0.001	2.87	0.005	1.33	0.111	6.36
CURM 51.13-4		88.79	0.270	0.104	0.335	0.057	0.022	1.81	0.174	0.898	0.215	7.30
CURM 51.14-4		88.57	0.113	0.003	0.656	0.219	0.012	0.72	0.286	0.55	0.44	8.42
CURM 52.52-5		79.26	0.044	0.074	0.094	3.56	...	6.02	0.011	0.145	10.69	...	0.007	0.004
CURM 52.54-4		81.59	0.135	0.086	0.39	5.40	...	3.31	0.022	1.20	7.85	...	<0.005	<0.005
CURM 54.01-4	Phosphor Brasses	95.42	3.17	0.307	0.346	0.348	0.053	0.028	0.039	0.158	0.044	0.070	...	0.040	0.023	0.008	
CURM 54.02-4		92.87	5.53	0.663	0.410	0.109	0.107	0.102	0.101	0.023	0.026	0.020	0.030	0.0020
CURM 54.03-4		91.74	7.30	0.003	0.003	0.0019	0.954	0.005	<0.002	<0.0005	0.006	0.0007	...	<0.001	<0.001	<0.0003
CURM 54.03-5		92.56	6.67	0.0012	<0.002	0.0006	0.786	0.015	<0.002	<0.0003	<0.001	<0.001	<0.001	<0.001	<0.001	<0.0003
CURM 54.04-4		86.54	9.47	0.79	1.09	0.536	0.250	0.316	0.065	0.419	0.106	0.33	...	0.074	0.046	0.0009
CURM 54.05-4		84.78	11.36	1.14	0.554	1.28	0.501	0.051	0.006	0.078	0.063	0.111	...	0.055	0.063	0.0021
CURM 62.12-4	Cupro-Nickel	89.42	0.111	0.053	0.180	7.94	...	0.45	0.109	1.59	0.034	0.002	0.081	
CURM 71.31-5	Leaded Gunmetals	83.00	4.06	6.07	3.98	1.98	0.060	0.118	0.020	0.037	0.110	0.128	0.030	0.023	0.059	...	0.039	0.046	...
CURM 71.32-5		82.69	6.07	4.14	6.02	0.570	<0.001	0.056	<0.001	<0.0005	0.213	<0.002	<0.002	<0.001	0.082	...	<0.0005	0.029	...
CURM 71.33-8		83.60	4.96	6.84	3.60	0.938	<0.001	0.018	<0.005	<0.0005	<0.001	<0.002	<0.002	<0.001	<0.001	<0.001	<0.0005	<0.002	...

SETTING-UP SAMPLES FOR DIRECT READING SPECTROGRAPHS

These samples have been thoroughly examined both spectrographically and chemically to confirm the homogeneity of the bulk samples. Their compositions have NOT, however, been accurately determined since it is not intended that they should be used as Spectroscopic Standard CRMs or as RMs. An Information Sheet is supplied with each sample giving the approximate composition.

Carbon, Low Alloy and Stainless Steels (Wrought) (Approx. 44mm dia. x 25, 75 or 150mm lengths)

Ref. No.	Description	Approximate Chemical Compositions (mass content in %)																					
		C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Sn	Ti	V	W	Zr	Ca	Others
SUS A/11	Low Carbon Steel	0.02	0.01	0.15	<0.005	0.005	0.02	0.01	0.05	0.07	0.01	0.01	...	<0.005	<0.005	<0.001	<0.005	<0.005
SUS B/6	Low Alloy Steel	0.39	0.29	0.44	0.005	<0.005	1.2	0.20	1.5	0.01	0.005	0.001	0.02	0.15	...	0.005	0.01	0.01	0.01	0.005	...	<0.001	<0.001 Pb
SUS C/18	Low Alloy Steel	0.15	0.18	1.2	0.07	0.06	0.18	0.11	3.5	0.05	...	0.01	0.06	0.46	0.005	0.02	0.06	0.03	0.43	0.33	0.05	0.001	...
SUS D/11	Low Alloy Steel	0.80	0.80	0.40	0.01	0.03	3.0	1.3	0.10	0.19	...	<0.001	0.29	0.11	0.01	0.05	0.01	0.10	0.12	0.16
SUS E/6	Highly Alloyed Steel	0.07	0.69	1.5	0.006	0.003	14.8	1.3	25.3	0.21	...	0.005	0.09	0.01	0.01	<0.1	...	2.1	0.31	0.04	53.7 Fe
SUS F/5	Duplex Stainless Steel	0.02	0.26	0.50	0.02	<0.005	24.7	3.5	7.0	<0.005	0.005	0.002	0.01	0.59	0.23	<0.005	<0.001	<0.005	0.03	0.62	62.9 Fe
SUS G/6	Stainless Steel	0.02	0.22	1.5	0.03	0.03	16.9	2.1	11.0	0.003	0.11	0.35	0.04	<0.001	0.008	0.003	0.05	0.06	<0.001	0.002	<0.002 Ta

Cast Irons (Approx. 60mm x 35mm x 18mm chill cast blocks.) These samples have been prepared jointly by Castings Technology International (formerly BCIRA) and BAS

Ref. No.	Description	Approximate Chemical Compositions (mass content in %)																		
		C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Cu	Sn	Ti	V	Bi	Mg	Sb	Ce
SUS 1/19	Low Phosphorus Iron	3.1	2.8	0.44	0.05	0.07	0.50	0.33	0.19	0.02	0.47	0.05	<0.005	0.04
SUS 2/43	Medium Phosphorus Iron	3.5	1.8	0.81	0.18	0.13	0.08	0.10	0.49	<0.005	0.19	0.09	0.05	0.52
SUS 3/20	High Phosphorus Iron	3.3	2.2	0.92	1.0	0.10	0.26	<0.005	0.03	<0.005	0.03	<0.005	0.12	0.30
SUS 4/24	Ductile (Nodular) Iron	3.3	2.6	0.12	...	0.01	0.09	...	0.09	0.01	0.07	...	0.74	<0.005	0.06	0.51	...	0.02	<0.005	...
SUS 5/46	Ductile (Nodular) Iron	3.8	2.1	0.65	...	0.009	0.02	...	1.0	0.04	<0.005	...	0.005	0.07	<0.005	0.52	...	0.08	0.05	0.04
SUS 6/6	Malleable Iron	2.5	1.8	0.65	0.05	0.12	0.10	<0.005	...	<0.001	0.02	0.05	0.02	0.02	0.01
SUS 7/8	Malleable Iron	2.8	0.94	0.29	0.09	0.18	0.07	0.02	...	0.004	0.21	<0.01	...	0.06	<0.001

NUMERICAL INDEX (Including Certification Dates)

Certificates may be reprinted from time to time to accommodate updated text or statistical treatment. In certain cases, where chemical analyses carried out after issuance of the original certificate lead to additional or revised certified data, the "Date of Latest Certificate" below is stated in bold. If the certificate in your possession is not the current one, we shall gladly supply this to you on request.

BRITISH CHEMICAL STANDARD CRMs		Date of Latest Certificate	Page
Ref. No.	Description		
BCS-CRM 111	Low Carbon Steel	Nov 04	7
BCS-CRM 112	Low Alloy Steel	Jul 04	9
BCS-CRM 113	Low Alloy Steel	Jul 04	9
BCS-CRM 114	Low Alloy Steel	Jul 04	9
BCS-CRM 159/3 (ECRM 055-1)	0.5% Carbon Steel	Dec 75	7
BCS-CRM 161/4	0.8% Carbon Steel	May 06	7
BCS-CRM 163/2 (ECRM 063-1)	1.2% Carbon Steel	Feb 72	7
BCS-CRM 176/2	Manganese Ore	Dec 79	14
BCS-CRM 177/2	Lead Base White Metal	Sep 77	13
BCS-CRM 178/2	Tin Base White Metal	Mar 76	13
BCS-CRM 179/2	High Tensile Brass	Apr 75	12
BCS-CRM 180/2	Copper-Nickel	Mar 76	12
BCS-CRM 181/3	2.5% Cu Aluminium Alloy	Sep 84	12
BCS-CRM 182/3	11% Si Aluminium Alloy	Apr 88	12
BCS-CRM 183/4	Leaded Gunmetal	Mar 84	12
BCS-CRM 206/3 (ECRM 453-1)	High Si and P Cast Iron	Oct 72	11
BCS-CRM 207/2	Gunmetal	May 76	12
BCS-CRM 214/2 (ECRM 152-1)	Mn-Mo Steel	Sep 04	9
BCS-CRM 216/3	5% Cu Aluminium Alloy	Oct 89	12
BCS-CRM 219/4 (ECRM 153-1)	Ni-Cr-Mo Steel	Feb 03	9
BCS-CRM 220/2 (ECRM 254-1)	High Speed Steel	Jan 71	8
BCS-CRM 222/1 (ECRM 154-1)	3% Ni Steel	Dec 77	9
BCS-CRM 225/2 (ECRM 155-1)	Ni-Cr-Mo Steel	Apr 64	9
BCS-CRM 232/2 (ECRM 051-1)	0.1% Sulphur Carbon Steel	Oct 70	7
BCS-CRM 236/3 (ECRM 454-1)	Hematite Iron	May 68	11
BCS-CRM 237/2 (ECRM 060-1)	0.1% Carbon Steel	Dec 75	7
BCS-CRM 238/2 (ECRM 061-1)	0.2% Carbon Steel	Apr 68	7
BCS-CRM 241/2 (ECRM 251-1)	High Speed Steel	Dec 75	8
BCS-CRM 242/2 (ECRM 555-1)	Ferro-Tungsten	Mar 85	11

BRITISH CHEMICAL STANDARD CRMs		Date of Latest Certificate	Page
Ref. No.	Description		
BCS-CRM 262/1	10% Mg Aluminium Alloy	Aug 78	12
BCS-CRM 263/2	5% Mg Aluminium Alloy	Jul 75	12
BCS-CRM 268/1	5% Si Aluminium Alloy	Apr 81	12
BSC-CRM 270 (ECRM 054-1)	0.09% Phosphorus Carbon Steel	Nov 75	7
BCS-CRM 290/2 (ECRM 253-1)	13% Manganese Steel	Feb 73	10
BCS-CRM 300/1	6% Zn Aluminium Alloy	Mar 74	12
BCS-CRM 301/1 (ECRM 651-1)	Lincolnshire Iron Ore	May 75	14
BCS-CRM 304/1	Copper Aluminium	Oct 79	12
BCS-CRM 307	Ce-Zn-Zr Magnesium Alloy	Jan 63	12
BCS-CRM 308	Grecian Chrome Ore	Apr 68	14
BCS-CRM 309	Sillimanite	Jul 74	15
BCS-CRM 310/1	Nimonic 90	Sep 69	13
BCS-CRM 313/1	High Purity Silica	Apr 89	15
BCS-CRM 316	8% Al Magnesium Alloy	Dec 69	12
BCS-CRM 317 (ECRM 151-1)	Low C High Si Steel	Oct 89	9
BCS-CRM 318A	0.01% O Steel	Sep 76	8
BCS-CRM 318B	0.01% O Steel	Sep 80	8
BCS-CRM 319/1	Magnesia	Feb 02	15
BCS-CRM 332	Austenitic Stainless Steel	Jun 66	10
BCS-CRM 339	Ferritic Stainless Steel	Feb 68	10
BCS-CRM 340	Ferritic Stainless Steel	Feb 68	10
BCS-CRM 341	Ferritic Stainless Steel	Feb 68	10
BCS-CRM 342	Ferritic Stainless Steel	Feb 68	10
BCS-CRM 343	Wrought Aluminium Alloy	May 86	12
BCS-CRM 344	70/30 Brass	Oct 81	12
BCS-CRM 345	Nickel Alloy IN100	Jun 03	13
BCS-CRM 346	Nickel Alloy IN100	Jun 03	13
BCS-CRM 347	Electronic Flowsolder	Jan 88	13

NUMERICAL INDEX (Including Certification Dates)

BRITISH CHEMICAL STANDARD CRMs		Date of Latest Certificate	Page
Ref. No.	Description		
BCS-CRM 348	Ball Clay	May 89	15
BCS-CRM 349	3.5% Cu Aluminium	Oct 89	12
BCS-CRM 350	Nickel Alloy IN713	Nov 05	13
BCS-CRM 351	Nickel Alloy IN718	Nov 05	13
BCS-CRM 352/1	Tungsten Carbide	Mar 02	14
BCS-CRM 353	Sulphate Resisting Portland Cement	Feb 90	13
BCS-CRM 354	White Portland Cement	Feb 90	13
BCS-CRM 355	Tin Ore	Sep 90	14
BCS-CRM 356	Titanium Alloy	Jan 94	13
BCS-CRM 357	Titanium Alloy	Jan 94	13
BCS-CRM 358	Zirconia	Jun 94	15
BCS-CRM 359	Nitrogen Bearing Silicon Carbide	Jun 96	14
BCS-CRM 360	Sialon Bonded Silicon Carbide	Jun 96	14
BCS-CRM 361	Chromium Metal	May09	13
BCS-CRM 362	Mine Tailings Sample	Sep 10	15
BCS-CRM 363/1	Monel Alloy 400	Oct 85	13
BCS-CRM 364	Leaded Bronze	Mar 73	12
BCS-CRM 369	Magnesite Chrome	Oct 71	15
BCS-CRM 370	Magnesite Chrome	Oct 71	15
BCS-CRM 371	Commercial Nickel	May 73	13
BCS-CRM 374	Phosphor Bronze	Jul 73	12
BCS-CRM 375/1	Soda Feldspar	Nov 04	15
BCS-CRM 376/1	Potash Feldspar	May09	15
BCS-CRM 380/1	2% Si Aluminium Alloy	Jul 89	12
BCS-CRM 381	Basic Slag	Jul 73	14
BCS-CRM 383	Alcomax III	Dec 77	11
BCS-CRM 385	Leaded Brass	Feb 75	12
BCS-CRM 387/1	Nimonic 901 Alloy	Jan 91	13
BCS-CRM 388	Zircon	Jul 93	15
BCS-CRM 389/1	High Purity Magnesia	Feb 02	15
BCS-CRM 390	High Tensile Brass	Oct 74	12
BCS-CRM 392	Fluorspar	Jun 79	14

BRITISH CHEMICAL STANDARD CRMs		Date of Latest Certificate	Page
Ref. No.	Description		
BCS-CRM 393 (ECRM 752-1)	Limestone	Jun 84	15
BCS-CRM 395	Bauxite	Jul 89	14
BCS-CRM 396	Low Silica Magnesite Chrome	May 84	15
BCS-CRM 398	Alnico H C	Jul 91	11
BCS-CRM 399	Phosphorus Deoxidised Copper	May 87	12
BCS-CRM 405	Low Alloy Steels	Jan 10	9
BCS-CRM 408	Low Alloy Steel	Jan 10	9
BCS-CRM 404/1,405/1	Low Alloy Steels	Dec 09	9
BCS-CRM 401/2-405/2	Low Alloy Steels	Dec 05	9
BCS-CRM 407/1-409/1	Low Alloy Steels	Dec 09	9
BCS-CRM 406/2-410/2	Low Alloy Steels	Feb 06	9
BCS-CRM 421-424	Low Tungsten Steels	May 74	9
BCS-CRM 431/2-435/2	Plain Carbon Steels	Jul 97	8
BCS-CRM 451/1-453/1	Carbon Steels - Residual Series (Gp A)	Sep 84	8
BCS-CRM 456/2-460/2	Carbon Steels - Residual Series (Gp B)	May 01	8
BCS-CRM 462, 463	Austenitic Stainless Steels	Jul 80	10
BCS-CRM 461/1, 462/1	Austenitic Stainless Steels	Jul 96	10
BCS-CRM 463/1, 465/1	Austenitic Stainless Steels	Jul 93	10
BCS-CRM 464/1	Austenitic Stainless Steel	Jul 90	10
BCS-CRM 466/2	Austenitic Stainless Steel	Dec 04	10
BCS-CRM 467/1, 468/1	Austenitic Stainless Steels	Jul 90	10
BCS-CRM 469-473	Ferritic Stainless Steels	Mar 85	10
BCS-CRM 474, 475	Stainless Steels	Jan 85	10
BCS-CRM 481-484	High Speed Steels	Feb 70	8
BCS-CRM 491, 494, 495	High Manganese Steels	Nov 72	10
BCS-CRM 495/1	High Manganese Steel	Oct 78	10
BCS-CRM 505,506	Aluminium-Silicon Alloys	Sep 85	12
BCS-CRM 512	Dolomite	Dec 04	15
BCS-CRM 513	Limestone	Dec 04	15
BCS-CRM 516	Standard Glass Sand	May 09	15
BCS-CRM 517	Brazilian Iron Ore	Dec 09	14

NUMERICAL INDEX (Including Certification Dates)

EURONORM CRMs		Date of Latest Certificate	Page
Ref. No.	Description		
ECRM 056-2(C)	0.8% Carbon Steel	May 09	7
ECRM 057-2(C)	0.05% Carbon Steel	Mar 99	7
ECRM 058-2(C)	0.15% Sulphur Steel	Aug 02	7
ECRM 059-2(C)	0.7% Carbon Steel	Nov 02	7
ECRM 064-1(C)	Nb/Ti Interstitial Free Steel	Nov 02	7
ECRM 084-1(C)	0.4% Carbon Steel	Feb 00	7
ECRM 085-1(C)	0.3% Sulphur Steel	Feb 03	7
ECRM 086-1(C)	0.3% Carbon Steel	Jan 01	7
ECRM 087-1(C)	0.15% Carbon Steel	Aug 07	7
ECRM 088-2	High Purity Iron	Jan 01	7
ECRM 090-1(C)	1% Carbon Steel	May 00	7
ECRM 091-1	0.5% Carbon Steel	Feb 05	7
ECRM 096-1(C)	Low S, Low Ca Steel	May 86	7
ECRM 096-2(C)	Low S, Ca-Treated Steel	Mar 99	7
ECRM 097-1(C)	High Purity Iron	Feb 98	7
ECRM 186-1(C)	Silico Manganese Steel	Jul 08	9
ECRM 195-1(C)	Cr-Mo-Ni Steel	Mar 92	9
ECRM 272-1(C)	12% Chromium Steel	Jul 05	10
ECRM 276-2(C)	5% Cr-Mo-V Steel	Feb 93	10
ECRM 281-1	18/9 Stainless Steel + Ti	Dec 82	10
ECRM 285-2(C)	Maraging Steel	May 97	10
ECRM 287-1(C)	High Boron Stainless Steel	Jul 04	10
ECRM 292-1(C)	Nb Stabilized Stainless Steel	Nov 90	10
ECRM 295-1(C)	4% Mo-Cr-Ni Steel	Mar 95	10
ECRM 296-1(C)	Jethete Steel	Mar 97	10
ECRM 376-1	24% Co Magnet Alloy	Nov 90	11
ECRM 451-2	Austenitic Cast Iron	Jan 99	11
ECRM 481-1	Nodular Iron	Aug 07	11
ECRM 482-2	Low Alloy Cast Iron	Jul 94	11
ECRM 483-1	High Duty Cast Iron	Sep 03	11
ECRM 484-1	Whiteheart Malleable Iron	Aug 02	11
ECRM 486-1	Foundry Iron	Mar 04	11
ECRM 489-1	White Iron	Dec 91	11
ECRM 576-1	Ferro-Niobium	May 84	11
ECRM 577-1	Ferro-Vanadium	Sep 80	11
ECRM 578-1	Ferro-Molybdenum	Nov 78	11
ECRM 579-1	Ferro-Niobium	May 83	11
ECRM 580-1	Ferro-Chromium	Jan 87	11
ECRM 583-1	Ferro-Manganese	May 84	11
ECRM 584-1	Ferro-Titanium	Jan 88	11
ECRM 585-2	High C, Ferro-Chromium	Jul 07	11
ECRM 587-1	Ferro-Boron	May 86	11
ECRM 590-1	Ferro-Tungsten	Mar 91	11
ECRM 676-1	Iron Ore Sinter	Nov 75	14
ECRM 681-1	Iron Ore	Oct 79	14
ECRM 682-2	Iron Ore	Apr 09	14
ECRM 683-1	Iron Ore Sinter	Aug 85	14
ECRM 776-1	Firebrick	May 83	15
ECRM 781-1	Silicon Carbide Refractory	Mar 93	14
ECRM 782-1	Dolomite	Jul 96	15
ECRM 783-1	Tungsten Carbide	Jul 05	14
ECRM 879-1	Basic Slag	Jun 82	14

SPECTROSCOPIC STANDARD CRMs		Date of Latest Certificate	Page
Ref. No.	Description		
SS-CRM 51,53,55,56	Carbon Steels – Residual Series	Jan 10	17
SS-CRM 70	Ferritic Stainless Steel	Feb 68	20
SS-CRM 111	Low Carbon Steel	Jul 04	18
SS-CRM 112-114	Low Alloy Steels	Jul 04	18
SS-CRM 310/1	Nimonic 90 Alloy	Sep 69	21
SS-CRM 345	Nickel Alloy IN100	Jun 03	21
SS-CRM 346A	Nickel Alloy IN100	Jun 03	21
SS-CRM 350	Nickel Alloy IN713	Nov 05	21
SS-CRM 351	Nickel Alloy IN718	Nov 05	21
SS-CRM 363/1	Monel Alloy 400	Oct 85	21
SS-CRM 387/1	Nimonic 901 Alloy	Jan 91	21
SS-CRM 401/2-405/2	Low Alloy Steels	Dec 05	18
SS-CRM 406/2-410/2	Low Alloy Steels	Feb 06	18
SS-CRM 421-424	Low Tungsten Steels	May 74	18
SS-CRM 432/1-435/1	Plain Carbon Steels	Jan 79	17
SS-CRM 431/2-435/2	Plain Carbon Steels	Jul 97	17
SS-CRM 453/1, 454/1	Carbon Steels - Residual Series (Gp A)	Sep 84	17
SS-CRM 458/1	Carbon Steel - Residual Series (Gp B)	May 95	17
SS-CRM 456/2-460/2	Carbon Steels - Residual Series (Gp B)	May 01	17
SS-CRM 462	Austenitic Stainless Steel	Jul 80	19
SS-CRM 461/1, 462/1	Austenitic Stainless Steels	Jul 96	19
SS-CRM 463/1, 465/1	Austenitic Stainless Steels	Jul 93	19
SS-CRM 466/2	Austenitic Stainless Steel	Dec 04	19
SS-CRM 464/1, 467/1, 468/1	Austenitic Stainless Steel	Jul 90	19
SS-CRM 469-473	Ferritic Stainless Steels	Mar 85	20
SS-CRM 475	Stainless Steel	Jan 85	19
SS-CRM 481/1-487/1	High Speed Tool Steels	May 84	20
SS-CRM 491/2	High Manganese Steel (Cast)	Aug 96	20
SS-CRM 492/3	High Manganese Steel (Cast)	May 10	20
SS-CRM 495/4	High Manganese Steel (Cast)	Apr 09	20
SS-CRM 601/2-605/2	Plain Carbon Cast Steels	Sep 90	19
SS-CRM 612/1, 614/1, 615/1	Low Alloy Cast Steels	Aug 84	18
ECRM 056-2(D)	0.8% Carbon Steel	Mar 09	17
ECRM 057-2(D)	0.05% Carbon Steel	Mar 99	17
ECRM 058-2(D)	0.15% Sulphur Steel	Aug 02	17
ECRM 059-2(D)	0.7% Carbon Steel	Nov 02	17
ECRM 064-1(D)	Nb/Ti Interstitial Free Steel	Nov 02	17
ECRM 084-1(D)	0.4% Carbon Steel	Feb 00	17
ECRM 085-1(D)	0.3% Sulphur Steel	Feb 03	17
ECRM 086-1(D)	0.3% Carbon Steel	Jan 01	17
ECRM 087-1(D)	0.15% Carbon Steel	Aug 07	17
ECRM 090-1(D)	1% Carbon Steel	May 00	17
ECRM 096-2(D)	Low S, Ca-Treated Steel	Mar 99	17
ECRM 097-1(D)	High Purity Iron	Feb 98	18
ECRM 186-1(D)	Silico Manganese Steel	Jul 08	18
ECRM 195-1(D)	Cr-Mo-Ni Steel	Mar 92	18
ECRM 272-1(D)	12% Chromium Steel	Jul 05	19
ECRM 276-2(D)	5% Cr-Mo-V Steel	Feb 93	19
ECRM 285-2(D)	Maraging Steel	May 97	19
ECRM 287-1(D)	High Boron Stainless Steel	Mar 04	19
ECRM 292-1(D)	Nb-Stabilized Stainless Steel	Nov 90	19
ECRM 295-1(D)	4% Mo-Cr-Ni Steel	Mar 95	19
ECRM 296-1(D)	Jethete Steel	Mar 97	19
SCRM 651/4-655/4	Malleable Irons	Jan 91	21
SCRM 656/8, 657/8, 659/8	Low Phosphorus Engineering Irons	Jul 94	21
SCRM 658/10	Low Phosphorus Engineering Iron	Jul 08	21
SCRM 660/9	Low Phosphorus Engineering Iron	Nov 05	21
SCRM 661/4-665/4	High Phosphorus Engineering Irons	Oct 93	21
SCRM 666/11	Ductile (Nodular) Irons	Jan 05	21
SCRM 667/12, 669/12	Ductile (Nodular) Irons	Nov 07	21
SCRM 668/11	Ductile (Nodular) Iron	Jun 05	21
SCRM 670/14	Ductile (Nodular) Iron	Jul 08	21
SCRM 671-675	Blast Furnace Irons	Jan 05	21

NUMERICAL INDEX (Including Certification Dates)

REFERENCE MATERIALS & SETTING-UP SAMPLES		Date of Latest Analysis Report or Information Sheet	Page
Ref. No.	Description		
BCS-RM 190t	Benzoic Acid	Aug 04	16
BCS-RM 192g	High Purity Tin (300g blocks)	Jan 87	16
BCS-RM 192h	High Purity Tin (millings)	Apr 01	16
BCS-RM 194e	High Purity Zinc (300g blocks)	Jul 75	16
BCS-RM 195g	High Purity Aluminium (300g blocks)	Aug 78	16
BCS-RM 195g	High Purity Aluminium (millings)	Aug 78	16
BCS-RM 198f	Super Pure Aluminium (100g blocks)	Dec 77	16
BCS-RM 201a	Nepheline Syenite	Mar 91	16
BCS-RM 202a	Plaster (Gypsum)	Mar 91	16
BCS-RM 203a	Talc	Mar 91	16
BCS-RM 204a	Zircon	Mar 91	16
BCS-RM 210e	High Purity Lead (500g bars)	Apr 71	16
LARM 1-5	Low Alloy Cast Irons	May 88	22
CRRM 1 & 3	High Chromium Irons	Feb 91	22
CRRM 1/1-5/1	High Chromium Irons	May 00	22
NCRM 1-5	Nickel Chromium Irons	May 95	22
NIRM 1, 3, 4, 5, 6 & 7	Austenitic (Ni-Resist) Irons	Jan 93	22
NIRM 2/1	Austenitic (Ni-Resist) Iron	Jun 10	22
NIRM 8/1	Austenitic (Ni-Resist) Iron	May 07	22
SIMO 1/2	Silicon Molybdenum Cast Iron	Nov 05	22
SIMO 2/2	Silicon Molybdenum Cast Iron	May 10	22
SUS A/11	Low Carbon Steel	Mar 06	24
SUS B/6	Low Alloy Steel	Oct 95	24
SUS C/18	Low Alloy Steel	Jan 07	24
SUS D/11	Low Alloy Steel	Aug 97	24
SUS E/6	Highly Alloyed Steel	Jul 08	24
SUS F/5	Duplex Stainless Steel	Aug 00	24
SUS G/6	Stainless Steel	Jun 00	24
SUS 1/19	Low Phosphorus Iron	Mar 08	24
SUS 2/43	Medium Phosphorus Iron	Mar 08	24
SUS 3/20	High Phosphorus Iron	Oct 06	24
SUS 4/24	Ductile (Nodular) Iron	Sep 08	24
SUS 5/46	Ductile (Nodular) Iron	Jul 09	24
SUS 6/6	Malleable Iron	Dec 93	24
SUS 7/8	Malleable Iron	May 95	24

SPECTROSCOPIC REFERENCE MATERIALS		Date of Latest Analysis Report	Page
Ref. No.	Description		
CURM 09.01-4	Phosphorus Deoxidised Copper	Sep 03	23
CURM 09.02-4	Phosphorus Deoxidised Copper	Sep 03	23
CURM 09.03-4	Phosphorus Deoxidised Copper	Sep 03	23
CURM 09.04-4	Phosphorus Deoxidised Copper	Sep 03	23
CURM 30.04-4	Main Elements in Brass	Jul 09	23
CURM 30.05-4	Main Elements in Brass	Jul 09	23
CURM 30.09-4	Main Elements in Brass	Sep 03	23
CURM 30.11-4	Main Elements in Brass	Sep 03	23
CURM 30.15-4	Main Elements in Brass	Sep 03	23
CURM 30.16-4	Main Elements in Brass	Sep 03	23
CURM 30.18-4	Main Elements in Brass	Sep 03	23
CURM 30.20-4	Main Elements in Brass	Sep 03	23
CURM 30.21-4	Main Elements in Brass	Sep 03	23
CURM 42.21-2	Admiralty & Naval Brass	Jul 09	23
CURM 42.22-2	Admiralty & Naval Brass	Jul 09	23
CURM 42.23.2	Admiralty & Naval Brass	Jul 09	23
CURM 42.24-2	Admiralty & Naval Brass	Jul 09	23
CURM 42.25-2	Admiralty & Naval Brass	Jul 09	23
CURM 43.01-4	Aluminium Brass	Sep 03	23
CURM 43.02-4	Aluminium Brass	Sep 03	23
CURM 48.01-1	Cartridge Brass	Sep 03	23
CURM 48.02-1	Cartridge Brass	Sep 03	23
CURM 48.04-1	Cartridge Brass	Sep 03	23
CURM 48.05-1	Cartridge Brass	Sep 03	23
CURM 50.01-4	Leaded Bronze	Sep 03	23
CURM 50.02-4	Leaded Bronze	Sep 03	23
CURM 50.03-4	Leaded Bronze	Sep 03	23
CURM 50.04-4	Leaded Bronze	Sep 03	23
CURM 51.11-4	Aluminium Bronze	Sep 03	23
CURM 51.12-4	Aluminium Bronze	Sep 03	23
CURM 51.13-4	Aluminium Bronze	Sep 03	23
CURM 51.14-4	Aluminium Bronze	Sep 03	23
CURM 52.52-5	Aluminium Bronze	Mar 09	23
CURM 52.54-4	Aluminium Bronze	Nov 08	23
CURM 54.01-4	Phosphor Bronze	Sep 03	23
CURM 54.02-4	Phosphor Bronze	Sep 03	23
CURM 54.03-4	Phosphor Bronze	Sep 03	23
CURM 54.03-5	Phosphor Bronze	May 10	23
CURM 54.04-4	Phosphor Bronze	Sep 03	23
CURM 54.05-4	Phosphor Bronze	Sep 03	23
CURM 62.12-4	Cupro-Nickel	Sep 03	23
CURM 71.31-5	Leaded Gunmetal	Sep 03	23
CURM 71.32-5	Leaded Gunmetal	Apr 09	23
CURM 71.33-8	Leaded Gunmetal	Jul 09	23

BAS

MIDDLESBROUGH

U.K.