

ECIIS
EUROPEAN COMMITTEE FOR IRON AND STEEL STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION DU FER ET DE L'ACIER
EUROPÄISCHES KOMITEE FÜR EISEN-UND STAHLNORMUNG
EUROPEAN CERTIFIED REFERENCE MATERIAL (EURONORM — CRM)
CERTIFICATE OF CHEMICAL ANALYSIS
EURONORM — CRM No. 489-1 WHITE CAST IRON

**LABORATORY MEANS (4 values)
mass content in %**

Line No.	C	Si	P	S	Cu	Mn*	N
1	2.8060	1.4997	0.7900	0.1468	0.2598	0.4920	0.0047
2	2.8188	1.5000	0.7904	0.1476	0.2640	0.4954	0.0049
3	2.8373	1.5070	0.7915	0.1498	0.2650	0.4965	0.0050
4	2.8433	1.5070	0.7975	0.1520	—	0.5003	0.0050
5	2.8482	1.5100	0.7984	0.1521	0.2697	0.5018	0.0051
6	2.8483	1.5135	0.8044	0.1525	0.2706	0.5035	0.0053
7	2.8495	1.5136	0.8070	0.1530	0.2710	0.5044	0.0054
8	2.8513	1.5137	0.8078	0.1532	0.2720	0.5052	0.0057
9	2.8553	1.5183	0.8085	0.1533	0.2725	0.5068	0.0057
10	2.8558	1.5200	0.8094	0.1541	0.2728	0.5074	0.0057
11	2.8573	1.5205	0.8120	0.1544	0.2730	0.5093	0.0057
12	2.8576	1.5253	0.8128	0.1545	0.2733	0.5100	0.0058
13	2.8579	1.5267	0.8152	0.1546	0.2736	0.5106	0.0058
14	2.8605	1.5279	0.8155	0.1553	0.2737	0.5108	0.0059
15	2.8630	1.5283	0.8186	0.1555	0.2741	0.5115	0.0060
16	2.8641	1.5293	0.8192	0.1559	0.2745	0.5128	0.0062
17	2.8659	1.5304	0.8193	0.1572	0.2759	0.5155	0.0063
18	2.8668	1.5329	0.8272	0.1574	0.2762	0.5175	0.0063
19	2.8693	1.5350	0.8281	0.1574	0.2773	0.5181	0.0064
20	2.8768	1.5355	0.8288	—	0.2775	0.5195	
21	2.8780	1.5367	0.8298	0.1583	0.2783	0.5203	
22	2.8828	1.5368	0.8345	0.1585	0.2828	0.5220	
23	2.8913	1.5403	0.8413	0.1590	0.2848	0.5313	
24	2.8955	1.5472	0.8572	0.1622	0.2868	—	
25	2.9037	1.5575		0.1641	—		
M_M	2.8602	1.5245	0.8152	0.1549	0.2739	0.510	0.0056
s_M	0.0218	0.0145	0.0166	0.0040	0.0062		
s_w	0.0106	0.0094	0.0072	0.0016	0.0023		

M_M: Mean of the intralaboratory means **s_M:** Standard deviation of the intralaboratory means

s_w: Mean intralaboratory standard deviation **s_b:** Interlaboratory standard deviation

$$s_M = \sqrt{s_b^2 + s_w^2/4}$$

The laboratory mean values have been examined statistically to eliminate any outlying values. Where a “—” appears in the table it indicates that an outlying value has been omitted by either the Cochran or Grubbs test.

* NOTE: The manganese content has not been certified because the sample was slightly contaminated with manganese during the grinding operation.

**CERTIFIED VALUES
mass content in %**

	C	Si	P	S	Cu
M_M C(95%)	2.860 0.009	1.524 0.006	0.815 0.007	0.155 0.002	0.274 0.003

The half width confidence interval C(95%) = $\frac{t \times s_M}{\sqrt{n}}$ where t is the appropriate Student's t value and n is the number of acceptable mean values

For further information regarding the confidence interval for the certified value see ISO Guide 35:1989 section 4.

DESCRIPTION OF THE SAMPLE

This sample consists of material passing a 400 µm aperture sieve from which the fines passing a 150 µm aperture sieve have been removed. It is supplied only in bottles of 100g

This reference material prepared and issued by:

BUREAU OF ANALYSED SAMPLES LIMITED

Newham Hall, Middlesbrough, England

On behalf of: The Iron and Steel Nomenclature Co-ordinating Committee (COCOR) of the ECISS, after approval by all the participating laboratories and all the producing organizations. (France—IRSID; German Federal Republic—Iron and Steel CRM Working Group; UK—BAS Ltd.)

DECEMBER 1991



PARTICIPATING LABORATORIES

Acerinox S.A., Algeciras (Spain)	Max-Planck Institut für Eisenforschung GmbH, Düsseldorf (Germany)
BCIRA, Birmingham (UK)	Midland Rollmakers Ltd., Crewe (UK)
Bundesanstalt für Materialforschung und -prüfung (BAM), Berlin (Germany)	Nordisk Analys Service AB (NASAB), Hälfors (Sweden)
Centre de Recherches de Pont à Mousson S.A. Maidières (France)	Rautaruukki Oy, Raahe (Finland)
Centre Technique des Industries de la Fonderie (CTIF), Sevres (France)	Ridsdale and Co. Ltd., Middlesbrough (UK)
Centro Nacional de Investigaciones Metalúrgicas (CENIM), Madrid (Spain)	Sollac, Florange (France)
Centro Sviluppo Materiali (CSM), Rome (Italy)	Svenskt Stål AB, Oxelösund (Sweden)
Cockerill Sambre S.A., Couillet (Belgium)	Staatliches Materialprüfungsamt Nordrhein-Westfalen (MPA-NRW), Dortmund (Germany)
Dantest, Copenhagen (Denmark)	Stanton plc, Nottingham (UK)
Hoogovens Groep BV, IJmuiden (Netherlands)	The Davy Roll Co. Ltd., Sheffield (UK)
Institutet för Metallforskning, Stockholm, (Sweden)	Thyssen Edelstahlwerke AG, Witten (Germany)
Institut de Recherches de la Sidérurgie Française (IRSID), Maizières-les-Metz (France)	Voest Alpine Stahl Linz GmbH, Linz (Austria)
Lorfonte, Uckange (France)	

METHODS USED EURONORM-CRM 489-1

Element	Line Number	Methods
C	1- 13-21 2- 3- 5- 6- 7- 8- 9-10-11-12-17-18-19-20-22-23-24 4-16 14-25 15	Combustion, gravimetric Combustion, infrared absorption Combustion, non-aqueous titration Combustion, conductometry Combustion, coulometric titration
Si	1- 4- 5- 6- 7- 8- 9-11-12-13-14-16-17-18-19-20 -21-22-23-24-25 2- 3-15 10	Gravimetric, dehydration with perchloric acid ICP-AES Photometric as molybdenum blue without extraction
P	1- 5- 9-10-22 2- 4- 8-16-18 3-15-20-23 6-11-12-14-21-24 7 13 17 19	Photometric as phosphovanadomolybdate after extraction Photometric as molybdenum blue without extraction Acidimetric titration of ammonium phosphomolybdate ICP-AES Photometric as molybdenum blue after extraction Gravimetric as lead molybdate, precipitation as ammonium phosphomolybdate Gravimetric as ammonium phosphomolybdate Photometric as phosphovanadomolybdate without extraction
S	1- 2- 3- 5- 6- 9-10-12-14-15-16-17-18-19-21-23-24 4 7- 8-11-22 13-25	Combustion, infrared absorption Combustion, acidimetric titration Gravimetric as BaSO ₄ without separation Combustion, conductometry
Cu	1- 2- 3- 5- 6- 9-10-12-15-16-17-18-21-22 2- 7-19-23-24 8 11 13 14 20	FAAS ICP-AES Photometric with bis-cyclohexanone oxalyldihydrazone Photometric with oxalyldihydrazide Photometric with cuproine, without extraction Titration with iodine, separation sulphide Photometric with cuproine, extraction
Mn	1- 3- 4-13-19-21 2- 7- 8-10-11-15-16-18-20 5- 6- 9-14 12-17 23	FAAS Photometric, periodate oxidation ICP-AES Photometric, persulphate oxidation Titration with arsenite, oxidation with persulphate
N	1-2-3-4-5-6-7-8- 9-10-12-13-14-15-16-17-18-19 11	Thermal conductivity, decomposition in graphite crucible Photometric with indophenol blue after distillation

Abbreviations:- FAAS - Flame Atomic Absorption Spectrometry
 ICP-AES - Inductively Coupled Plasma-Atomic Emission Spectrometry

FURTHER INFORMATION

For information regarding the preparation, certification and supply of these European Certified Reference Materials (EURONORM-CRMs) and the use of the statistical information given on this certificate, please refer to Information Circulars No. 1 (ECIIS) and No. 5 (ECSC), both of which are available from the national standards body in your country. (In the UK this is the BSI, 2 Park Street, London W1A 2BS).

Des informations complémentaires sur la fabrication, la certification et la distribution des Matériaux de Référence Certifiés Européens (EURONORM—MRC) ainsi que sur l'utilisation des informations statistiques données sur le certificat se trouvent dans les circulaires d'information No. 1 (ECIIS) et No. 5 (CECA). On peut se procurer ces deux circulaires auprès des organismes nationaux de normalisation. (Pour la France: AFNOR, Tour Europe - Cedex 7, 92080 Paris La Défense).

Angaben über Herstellung, Zertifizierung und Bezugsmöglichkeiten dieser Zertifizierten Europäischen Referenzmaterialien (EURONORM-ZRM) sowie über die Anwendung der in diesem Zertifikat enthaltenen statistischen Daten finden sich in den Mitteilung en Nr. 1 (ECIIS) und Nr. 5 (EGKS), beide zu beziehen durch die nationalen Normenorganisationen. (In Deutschland bei der Vertriebsstelle des DIN: Beuth-Verlag GmbH, Burggrafenstrasse 4-10, 1000 Berlin 30).